

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T

21003762-
İNG

02-21

TEST RESULTS

TENSILE STRENGTH; EN 29073-3:1996

Instron 5969 (Load: 50 kN), Strip Method.
Speed: 100 mm/min±10, Gauge length 200 mm.
Pre-load was not applied. Without wetting samples.
The average results are given for weft and warp direction of five samples
Performed in the conditioned room (20±2°C-65%±4).

Critical area

Wet ;

RESULT

Weft

65,2 N

Warp

143,9 N

REQUIREMENT

≥ 20N (Wet)

≥ 20N (Wet)

BURSTING STRENGTH;; ISO 13938-1:1999

SDL ATLAS M229 tester. Test area: 30.5 mm diameter
Rate of increase in volume; 29 cm³/min.
The average results are given of five samples.
Performed in the conditioned room (20±2°C-65%±4).

Critical area

Dry ;

RESULT

196,0 kPa

Height at Burst*

86,0 mm

REQUIREMENT

≥ 40 kPa (Dry)

**ZENMED TIBBİ CİHAZLAR
VE SAĞLIK ÜRÜNLERİ SAN. VE TİC. LTD.ŞTİ.**
Mahmutbey Mah. 2567.Sk. No:1 İş Yeri No:11,21
Bağcılar / İSTANBUL / TÜRKİYE
Tel: 0212 445 45 25 Tic.Sic.No: 794704
Güneşli V.D.: 997 067 1942