



Oxford-110

100% POLYESTER

110GSM / PLAIN 1/1



| | |
|---------------------|---|
| Fabric name | Oxford-110 |
| Fabric weight | 110 gsm ± 3% |
| Composition | 100% Polyester |
| Full width | 150 cm |
| Weave | plain 1/1 |
| WR | PU 1000 |
| Area of use | light workwear jackets and rain coats |
| Washing instruction |  |

WR properties

| | | | |
|---|------------------------------------|--------------|---------|
| 1 | Water resistance, water column, mm | DIN EN 20811 | > 1 000 |
|---|------------------------------------|--------------|---------|

Physical properties

| | | | warp | weft | |
|---|--|------------------|------------------|------|--|
| 1 | Tensile strength, N | ISO 13934-1:2013 | 2724 | 2621 | |
| 2 | Tearing strength, N | ISO 13937-3:2000 | 81 | 63 | |
| 3 | Dimensional Stability To Washing, max. | ISO 6330:2000 | 3.0% | 3.0% | |
| 4 | Abrasion Resistance | ISO 12947-2:2002 | > 10 000 | | |
| 5 | Pilling Resistance | ISO 12945-2:2000 | 3-4 | | |
| 6 | Colour Fastness To Washing (cotton+polyester) 60°C, min. | ISO 105-C06:2010 | | | |
| | | Colour change | ISO 105-C06:2010 | 4-5 | |
| | | Colour staining | ISO 105-C06:2010 | 3-4 | |
| 7 | Colour Fastness To Perspiration, min. | ISO 105-E04:2013 | | | |
| | | Colour change | 4-5 | | |
| | | Colour staining | 4-5 | | |
| 8 | Colour Fastness To Rubbing, min. | ISO 105-X12:2001 | | | |
| | | Dry | 4-5 | | |
| | | Wet | 2-3 | | |
| 9 | Colour Fastness To Light | ISO 105-B02:2013 | | | |

