

Umka Pak - GD3

Technical specification / Tehnička specifikacija

GRAMMAGE / GRAMATURA	THICKNESS / DEBLJINA	STIFFNESS / KRUTOST LW5°		STIFFNESS / KRUTOST TABER 15°	
		md	cd	md	cd
g/m ²	µm	mNm	mNm	mNm	mNm
230	280	8	4	4	2
250	310	12,7	5	6,4	2,5
280	355	18,4	7,4	9,2	3,7
300	385	22,4	9,5	11,2	4,8
320	410	27,9	11,4	14	5,7
350	445	35,9	14,4	17,1	6,9
400	520	51,7	20,3	24,6	9,7
450	585	70,3	30	33,5	14,3

*L&W figures are binding, Taber figures are indicative

*L&W pokazatelji su obavezujući, Taber pokazatelji su indikativni

TESTING METHOD / METOD TESTIRANJA	STANDARD	TOLERANCES / TOLERANCIJA
Brightness / Belina	ISO 2470	77 ± 1%
Grammage / Gramatura	ISO 536	± 2%
Thickness / Debljina	ISO 534	± 5%
Stiffness / Krutost	DIN 53122	-15%
Testing climate		23 ± 1°C 50 ± 2% RH
Recyclability	EN13430	in terms of the norm
Biodegradability	EN13432	in terms of the norm
RECOMMENDED PRINTING METHODS / PREPORUČENI METODI ŠTAMPE		
Offset, Flexo / Ofset štampa, Flexo štampa		

valid from 01.01.2020