

HI-KOTE C2S Gloss

Grammage	g/m ²	ISO536	90	100	105	115	120	128	130	140	150	157	170	200	210	250	260	300
Thickness	µm	ISO534	72	80	84	92	96	102	104	120	130	135	146	173	183	225	234	270
Brightness	%ISO	ISO2470	89	89	89	89	89	89	89	89.5	89.5	89.5	89.5	89.5	89.5	89.5	89.5	89.5
Opacity	%	ISO2471	92	93	93	94	95	96	96	98	98	98.5	98.5	98.5	98.5	98.5	98.5	98.5
Roughness	µm	ISO8791/4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.4	≤1.6
Gloss	%	T480	65	65	65	65	65	65	65	67	67	67	67	67	67	67	65	65

HI-KOTE C2S Matt

Grammage	g/m ²	ISO536	90	100	105	115	120	128	130	140	150	157	170	200	210	250	260	300
Thickness	µm	ISO534	76	84	90	100	104	110	111	134	148	155	168	200	210	250	260	283
Brightness	%ISO	ISO2470	89	89	89	89	89	89	89	89.5	89.5	89.5	89.5	89.5	89.5	89.5	89.5	89.5
Opacity	%	ISO2471	90	92	93	94	94	95	95	98	98	98.5	98.5	98.5	98.5	98.5	98.5	98.5
Roughness	µm	ISO8791/4	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.7	≤2.5	≤2.5	≤2.5	≤2.5	≤2.5	≤2.5	≤2.5	≤2.5	≤2.5
Gloss	%	T480	35	35	35	32	32	32	32	30	30	30	30	30	30	30	30	30

Remarks: 80-130gsm are supplied from Gold East Paper (Jiangsu) Co Ltd, Zhenjiang.

140-300gsm are supplied from Hainan Jinhai Pulp & Paper Co Ltd, Hainan.