



# ARCOSET

## description

White uncoated papers and boards, certify FSC<sup>®</sup>, made with E.C.F. pulp. Good look-through. Good on-press and printing performance.

## range

| size   | grain | substance |    |    |     |     |     |     |     |     |     |
|--------|-------|-----------|----|----|-----|-----|-----|-----|-----|-----|-----|
| 45x64  | LG    | 70        | 80 | 90 |     |     |     |     |     |     |     |
| 64x88  | LG    | 70        | 80 | 90 | 100 | 120 | 140 | 170 | 190 |     |     |
| 70x100 | LG    | 70        | 80 | 90 | 100 | 120 | 140 | 170 | 190 | 250 | 300 |

## technical features

ref. standard/instrument  
unit of measure

| substance        | VSA                | opacity  | roughness  | tensile strength |           |
|------------------|--------------------|----------|------------|------------------|-----------|
| ISO 536          | ISO 534            | ISO 2471 | ISO 8791-2 | ISO 1924         |           |
| g/m <sup>2</sup> | cm <sup>3</sup> /g | %        | ml/min     | KN/m             |           |
|                  |                    |          |            | long±10%         | cross±10% |
| 70 ± 3%          | 1,2                | 88 ± 2   | 220 ± 30   | 3,9              | 2,6       |
| 80 ± 3%          | 1,2                | 90 ± 2   | 220 ± 30   | 4,5              | 2,8       |
| 90 ± 3%          | 1,2                | 92 ± 2   | 220 ± 30   | 5,2              | 3,2       |
| 100 ± 3%         | 1,2                | 93 ± 2   | 220 ± 30   | 5,9              | 3,4       |
| 120 ± 3%         | 1,2                | 95 ± 2   | 220 ± 30   | 6,5              | 3,9       |
| 140 ± 3%         | 1,2                | 97 ± 2   | 220 ± 30   | 7,8              | 4         |
| 170 ± 3%         | 1,2                | –        | 230 ± 30   | 9,1              | 4,5       |
| 190 ± 4%         | 1,2                | –        | 230 ± 30   | 9,8              | 5,2       |
| 250 ± 5%         | 1,2                | –        | 230 ± 30   | 11,1             | 5,8       |
| 300 ± 5%         | 1,2                | –        | 230 ± 30   | 11,7             | 6         |

Brightness (col. White White) - ISO 2470 (R457) 108% ± 2  
Relative Humidity 50% ± 5 ref. TAPPI 502-98

## ecological features



ELEMENTAL  
CHLORINE  
FREE  
GUARANTEED



## notes

The product is completely biodegradable and recyclable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.