



ALKİM KÂĞIT SANAYİ ve TİCARET A.Ş.

Kemalpaşa Organize Sanayi Bölgesi, Kırövası Mevkii TR-35170 Kemalpaşa İzmir Türkiye
Tel: (232) 877 0606 – Faks: (232) 877 0605 – E-Mail: info@alkimkagit.com.tr – www.alkimkagit.com.tr

TEKNİK ÖZELLİKLER / Technical Specifications

80 gr/m² FOTOKOPİ KAĞIDI (Photocopy Paper)

ALLCOPY

TEST METODU TESTING METHOD

GRAMAJ (gr/m²)
BASIS WEIGHT (gr/m²)

80 ± 1,5

Tappi 410

NEM (%)
MOISTURE (%)

4,5 ± 0,5

Tappi 412

MUKAVEMET (m)
BREAKING LENGHT (m)

MD

4.500 min

Tappi 494

MUKAVEMET (m)
BREAKING LENGHT (m)

CD

2.000 min

Tappi 494

BEYAZLIK (%)
BRIGHTNESS

100,0 min

Tappi 525

SARILIK
YELLOWNESS

25,0 ± 2

Tappi 525

COBB (60 sn. gr/m²)
COBB (60 sec. gr/m²)

24 ± 4

Tappi 441

CIE
CIE

Digitally signed by Persin Nicolai
Date: 2021.02.10 11:30:07 EET
Reason: MoldSign Signature
Location: Moldova



48 ± 3

Tappi 525

