



Karadenizliiler Mah. Ordulu Cad. No: 82, 41140 PK334 Başiskele KOCAELİ / TÜRKİYE
Tel: 444 78 52 (444 - PTKB) +90 (262) 349 37 90 / 91 +90 (262) 349 25 50 / 51
Fax: +90 262 349 37 59
petekboru.com.tr info@petekboru.com.tr

MILLTEST CERTIFICATE
EN 10204 3.1

Date/Tarih : 6.12.2022
Certificate/Sertifika No : 5397

Customer/Müşteri: S.C. NIMFA - COM S.R.L.

Standart No/Norm: TS EN 10217- 5

Order No-LC No/Sipariş No: 6478

Pipe Type/Boru Tipi: SAWH


Item Pos. Sıra No:	Dimensions OdxWbXl Ölçüler	Pieces Adet	Total Length Metre
1	426,00 X 8,80	9	108,00
2	508,00 X 8,80	5	60,00
3	426,00 X 10,00	9	108,00
4	1016,00 X 10,00	2	24,00

HT bar/sec	BD	GBT	NDT	VD	US
70/5	30	OK	OK	OK	OK
57/10	30	OK	OK	OK	OK
46/10	30	OK	OK	OK	OK
37/10	30	OK	OK	OK	OK

Item Pos. Sıra No:	Bant N°-Heat No Döküm No:	V	Cu	Ni	Cr	Mo	Al	Nb	Ti	S	P	Mn	Si	C	Steel Grade	Temp.	Material			Weld		
		X100														Kalite	Sıcaklık °C	Re(N/mm²)	Rm(N/mm²)	A (%)	Re(N/mm²)	Rm(N/mm²)
1	124922	0,6	2,2	2,7	1,3	0,0	-	0,0	0,2	0,5	1,3	90,2	19,3	16,6	P265GH TC1	23 °c	382,6	552,3	36,8	472,84	592,5	22,5
2	915598	0,3	2,9	3,1	3,5	0,3	-	0,3	0,2	0,5	1,6	46,4	6,3	9,3	P235GH TC1	23 °c	326,7	435,6	37,4	326,67	483,6	26,0
3	235402	0,1	1,6	2,9	2,2	0,0	-	0,0	0,1	0,3	1,6	108,7	18,5	15,7	P265GH TC1	23 °c	406,1	532,7	32,9	418,89	550,3	26,3
4	235402	0,1	1,6	2,9	2,2	0,0	-	0,0	0,1	0,3	1,6	108,7	18,5	15,7	P265GH TC1	23 °c	432,6	560,2	35,3	453,22	590,6	25,3

OD: Dış Çap / Outside Diameter
WT: Et Kalınlığı / Wall Thickness
BD: Havşa Açısı / Bevel Degree
VD: Göz/Ebat Kontrol / Visual Dimension

Re: Akma dayanımı / Yield Stress
Rm: Çekme Dayanımı / Tensile Strength
A%: Uzama / Elongation
GBT: Eğme testi/Guided Bend Test
HT: Hidrotest / Hydrostatic Test
N.D.T.: Tahribatsız test / Non-Destructive Testing
US: Ultrasonic test as per TS EN ISO 10893-11



ISO 9001:2015
ISO 14001:2015
ISO 45001:2018

