

## **COATED 80 FSC<sup>TM</sup> / P1000 / YG60**

PRODUCT DESCRIPTION / BENEFITS	Face : White, semigloss, woodfree, coated on one side paper.         Adhesive : General purpose permanent acrylic water based adhesive. Good adhesion to a wide variety of substrates, including non-polar surfaces. Good behaviour at low temperatures.         Liner : Honey supercalendered glassine paper one side sili-
	conised. There may be slight variations in tone.
TYPICAL USE	<ul> <li>Food</li> <li>Health &amp; Personal Care</li> <li>Transport &amp; Logistics</li> </ul>
PRINTING & CONVERTING	Suitable for printing in Flexography, Offset, Screen, hot-foil and Thermal Transfer. Testing for suitability between media, printers and inks is always recommended prior to use.
PRODUCT RECOMMENDATIONS	Machine coated paper for high quality labels. Ideal for multicolour prints requiring exceptional contrast and great detail.
SHELF LIFE	2 years, under storage conditions as defined by FINAT section 2.5 (20-25°C, 40-50% RH).Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life of the product.

#### FEDRIGONI SELF-ADHESIVES

# COATED 80 FSC<sup>™</sup> / P1000 / YG60

PHYSICAL PROPERTIES / TYPICAL VALUES

FACE MATERIAL					
COATED 80 FSC™					
Grammage	78 Gr/m2	ISO 536			
Thickness	64 µm	ISO 534-80			

ADHESIVE			
P1000			
Tack (N) Glass	11 N/mm	FTM9	
Min Labelling temperature	0°C		
Usage Temperature	-20/+70 °C		

LINER		
YG60		
Grammage	55 Gr/m2	ISO 536
Thickness	48 µm	ISO 534-80

### QUALITY CERTIFICATIONS & APPROVALS

IONS • Suitable for direct food contact with dry and moist, non-fatty food according to the Regulation (EU) No. 10/2011

FSC License code: FSC-C106281

#### DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.