



M4061 ACI

yellow
navy blue
red

WEAVE	Special Texture	COMPOSITION	75% mete-aramid 23% Para-aramid 2% anti-static fiber
WEIGHT g/m²	200(±5%)	USABLE WIDTH cm	150(±1%)

PHYSICALS SPECIFICTIONS

TEST ITEM	ISO	WARP	WEFT
Tensile strength /N	ISO 13934.1	≥650	≥650
Tearing strength /N	ISO 13937.3	≥100	≥100

FLAME RESISTANCE

TEST ITEM	Original	50times washing
Afterflame Time /s	0	0
Carbon Length /mm	≤60	≤60
Burning feature	no melt or drip	no melt or drip

COLOURS FASTNESS

TEST ITEM	ISO	Change	Stain	
			Cotton	PES
Washing at 60°C	ISO 105-C06	4	4	4
Perspiration	ISO 105-E04	4	4	4
Dry Rubbing	ISO 105-X12	4		
Wet Rubbing	ISO 105-X12	4		
Light	ISO 105-B02	4		

OTHERS

Dimensional Stability after 5 Washings at 40°C ISO 6330 Cycle 5A (40°C)	WARP ≤3	WEFT ≤3
Water Repellency	GB/T 4745 Original ≥4	After 5times washing ≥3

COMMENTS

The indicated figures are average values given for information only

BW Protect – Floor11, Building2, financial street(chang'an)center, Shijingshan district, Beijing, China(100043)