

**Technical characteristics
Office paper
SvetoCopy, grade C**

| Parameters | Target | |
|---------------------------|---------|----|
| Basis weight, gsm | 80 | ±3 |
| Caliper, μm | 104 | ±2 |
| Stiffness MD, mN | >105 | |
| Stiffness CD, mN | >45 | |
| Roughness TS/WS, ml/min | <300 | |
| Whiteness CIE, % | 146 | ±3 |
| Opacity, % | >91 | |
| Dennison surface strength | >14 | |
| Cobb 60 s, gsm | 20-30 | |
| Moisture, % | 3,9-5,3 | |
| Ash content, % | >18 | |

Number of sheets: 500 ±2%

Sheet size: A4 – 210x297 mm; A3 – 420x297 mm

Sheet size variation: < ±0,5 mm, squareness < ±0,5 mm

Management system is complies with ISO 9001, ISO 14001, ISO 45001

Production manager

Dmitri Korotayev



ECF