

Umka Pak GD3

Technical Specification

Tehnička Specifikacija



Grammage / Gramatura	Thickness / Debljina	Stiffness / Krutost LW5 ⁰	
		md	cd
g/m ²	µm	mNm	mNm
230	280	8	4
250	310	12,7	5
280	355	18,4	7,4
300	385	22,4	9,5
320	410	27,9	11,4
350	445	35,9	14,4
400	520	51,7	20,3
450	585	70,3	30

Testing method / Metod Testiranja	Standard	Tolerances / Tolerancija
Brightness / Belina	ISO 2470	77±1%
Grammage / Gramatura	ISO 536	±2%
Thickness / Debljina	ISO 534	±5%
Stiffness / Krutost	DIN 53122	85%
Testing climate		24 ± 1 ⁰ C 51 ± 2% RH

Recommended printing methods / Preporučeni metodi štampe: Offset, Flexo / Ofset štampa, Flexo štampa

Valid from 03/2015

Umka DOO Beograd, 13. Oktobra 1, 11260 Umka

Tel: +381 11 36 02 600, Fax: +381 11 8026 995

Email: sales@umka.rs web: www.umka.rs

All figures mentioned above may be subject to technical changes.