



VWR Brand Autoclave Bags

VWR CATALOG NUMBERS:

[Manufacturing country of origin for all below: USA, HS code 392329]

2 mil (50.8μ) PP			3.0 mil (76μ) PP		
VWRI 129-1555	200 x 305	Red Biohazard	VWRI 129-0030	305 x 610	Red Biohazard
VWRI 129-0033	305 x 610	Red Biohazard	VWRI 129-1560	610 x 760	Red Biohazard
VWRI 129-1556	480 x 610	Red Biohazard	VWRI 129-0031	950 x 914	Red Biohazard
VWRI 129-1557	610 x 760	Red Biohazard	VWRI 129-0032	950 x 1220	Red Biohazard
VWRI 129-0034	635 x 889	Red Biohazard	4.0 mil (102μ) PP		
VWRI 129-0035	610 x 914	Red Biohazard	VWRI 129-1561	610 x 914	Red Biohazard
VWRI 129-0036	950 x 1220	Red Biohazard	VWRI 129-1562	787 x 1016	Red Biohazard
VWRI 129-1558	787 x 914	Red Infectious Waste			

DESCRIPTION:

VWR Autoclavable Biohazard bags made from Suprop® Polypropylene film, specifically engineered to exhibit seal ability, exceptional toughness and excellent autoclavable temperature resistance (typical program of 20 mins. @ Operating temperature to 135°C, film will melt above 149°C) as utilized in some packaging and sterilization applications. All bags contain a temperature indicator patch which shows after processing “Contents Have Been Autoclaved”.

TYPICAL PRODUCT CHARACTERISTICS:

Values expressed below for available nominal film thicknesses.

PROPERTIES		2 mil (50.8μ)	3.0 mil (76μ)	4.0 mil (102μ)	Units	Test Method
Elmendorf Tear Resistance *	MD ↕	600	600	600	grams	ASTM D1922
	TD ↔	900	940	980	grams	
Dart Impact Strength		>1400	>1000	>800	grams	ASTM D1709
Coefficient of Friction		<0.20	<0.20	<0.20		ASTM D1894
Yield		15300	10200	7650	sq.in./lb.	Spartech-Tufpak

FOR YOUR PROTECTION:

The information and recommendations in this publication are, to the best of our knowledge, accurate and reliable. Suggestions made concerning uses or applications are only the opinion of Spartech-Tufpak, and users should make their own tests to determine the suitability of these products for their own purposes. However, because of numerous factors affecting results, Spartech-Tufpak. makes no warranty of any kind, express or implied, including those of merchantability and fitness for purpose, other than that the material conforms to its Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Spartech-Tufpak. for claims arising out of breach of warranty, negligence, strict liability, or otherwise is limited to the purchase price of the material. Statements concerning the use of products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is assumed. 1/2022