



## CALIBRE™ 303EP-22 Polycarbonate Resin

### Overview

CALIBRE™ 300EP-22 Series are polycarbonate resins that offer exceptional impact resistance, heat distortion resistance, and optical clarity for injection molding applications. Their high melt flow rate allows complex parts to be easily molded. The CALIBRE 300EP-22 series products are available in 4 additive packages: CALIBRE 300EP: No mold release or UV Stabilizer. CALIBRE 301EP: Mold release. CALIBRE 302EP: UV stabilizer. CALIBRE 303EP: Mold release and UV stabilizer.

#### Govt. and Industry Standards:

- CSA (Canadian Standards Association)
- Underwriters Laboratory, Inc. (UL)

#### Applications:

- Appliances
- Storage
- Electrical components
- Light diffusers

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>	ASTM D792 ISO 1183/B
Melt Index (300°C/1.2 kg)	22 g/10 min	22 g/10 min	ASTM D1238 ISO 1133
Molding Shrinkage - Flow	0.0050 to 0.0070 in/in	0.50 to 0.70 %	ASTM D955 ISO 294-4
Water Absorption			ASTM D570
73°F (23°C), 24 hr	0.15 %	0.15 %	
Equilibrium, 73°F (23°C), 50% RH	0.32 %	0.32 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus			
--	340000 psi	2340 MPa	ASTM D638 <sup>1</sup>
--	334000 psi	2300 MPa	ISO 527-2/50
Tensile Strength			
Yield	8700 psi	60.0 MPa	ASTM D638 <sup>1</sup> ISO 527-2/50 <sup>1, 1</sup>
Break	9500 psi	65.5 MPa	ASTM D638 <sup>1</sup>
Break	9430 psi	65.0 MPa	ISO 527-2/50
Tensile Elongation			ISO 527-2/50
Yield	6.0 %	6.0 %	ASTM D638 <sup>1</sup>
Break	120 %	120 %	ASTM D638 <sup>1</sup>
Flexural Modulus			
--	350000 psi	2410 MPa	ASTM D790 <sup>2</sup>
--	348000 psi	2400 MPa	ISO 178 <sup>3</sup>
Flexural Strength			
--	14000 psi	96.5 MPa	ASTM D790 <sup>2</sup>
--	14100 psi	97.0 MPa	ISO 178 <sup>3</sup>
Taber Abrasion Resistance	45 %	45 %	ASTM D1044
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	9.5 ft·lb/in <sup>2</sup>	20 kJ/m <sup>2</sup>	ISO 179/1eA

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			
73°F (23°C)	14.0 ft-lb/in	747 J/m	ASTM D256
73°F (23°C)	35.2 ft-lb/in <sup>2</sup>	74.0 kJ/m <sup>2</sup>	ISO 180/A
Instrumented Dart Impact			ASTM D3763 <sup>4</sup>
73°F (23°C), Total Energy	640 in-lb	72.3 J	
Tensile Impact Strength	180 ft-lb/in <sup>2</sup>	378 kJ/m <sup>2</sup>	ASTM D1822
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness			ASTM D785
M-Scale	73	73	
R-Scale	118	118	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Annealed	288 °F	142 °C	ASTM D648 ISO 75-2/B
264 psi (1.8 MPa), Unannealed	258 °F	126 °C	ASTM D648
264 psi (1.8 MPa), Unannealed	252 °F	122 °C	ISO 75-2/A
264 psi (1.8 MPa), Annealed	282 °F	139 °C	ASTM D648 ISO 75-2/A
Vicat Softening Temperature	297 °F	147 °C	ISO 306/B50 ASTM D1525 <sup>5</sup>
Ball Indentation Temperature	257 °F	125 °C	IEC 60335-1
CLTE - Flow (-40 to 180°F (-40 to 82°C))	0.000038 in/in/°F	0.000068 cm/cm/°C	ASTM D696
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Volume Resistivity	2.0E+17 ohm-cm	2.0E+17 ohm-cm	ASTM D257
Dielectric Strength	420 V/mil	17 kV/mm	ASTM D149
Dielectric Constant			ASTM D150
60 Hz	3.00	3.00	
1 MHz	3.00	3.00	
Dissipation Factor			ASTM D150
50 Hz	0.0010	0.0010	
1 MHz	0.0020	0.0020	
Comparative Tracking Index			IEC 60112
0.0787 in (2.00 mm), Solution A	250 V	250 V	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating - UL			UL 94
0.0625 in (1.59 mm)	V-2	V-2	
0.125 in (3.18 mm)	V-2	V-2	
Oxygen Index	26 %	26 %	ISO 4589-2
Average Extent of Burning	1 in	3 cm	ASTM D635
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Refractive Index	1.586	1.586	ASTM D542 ISO 489
Transmittance	89.0 %	89.0 %	ASTM D1003
Haze	1.0 %	1.0 %	ASTM D1003

#### Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

<sup>1</sup> Type I, 2.0 in/min (51 mm/min)

<sup>2</sup> Method I (3 point load), Type I, 0.079 in/min (2.0 mm/min)

<sup>3</sup> 0.079 in/min (2.0 mm/min)

<sup>4</sup> 11.1 ft/sec (3.39 m/sec)

<sup>5</sup> Rate A (50°C/h), Loading 2 (50 N)

## Product Stewardship

Styron LLC, Styron HoldCo B.V., and subsidiaries ("Styron") have a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Styron products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Styron strongly encourages its customers to review both their manufacturing processes and their applications of Styron products from the standpoint of human health and environmental quality to ensure that Styron products are not used in ways for which they are not intended or tested. Styron personnel are available to answer your questions and to provide reasonable technical support. Styron product literature, including safety data sheets, should be consulted prior to use of Styron products. Current safety data sheets are available from Styron.

## Medical Applications Policy

**NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS:** Styron will not knowingly sell or sample any product or service ("Product") into any commercial or developmental application that is intended for:

- long-term or permanent contact with internal bodily fluids or tissues. "Long-term" is contact which exceeds 72 continuous hours;
- use in cardiac prosthetic devices regardless of the length of time involved ("cardiac prosthetic devices" include, but are not limited to, pacemaker leads and devices, artificial hearts, heart valves, intra-aortic balloons and control systems, and ventricular bypass-assisted devices);
- use as a critical component in medical devices that support or sustain human life; or
- use specifically by pregnant women or in applications designed specifically to promote or interfere with human reproduction.

Styron requests that customers considering use of Styron products in medical applications notify Styron so that appropriate assessments may be conducted.

Styron does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Styron product is safe, lawful, and technically suitable for the intended use. **STYRON MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY STYRON PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

## Disclaimer

**NOTICE:** No freedom from infringement of any patent owned by Styron or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Styron assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

**NOTICE:** If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Styron to change specifications and/or discontinue production; and (4) although Styron may from time to time provide samples of such products, Styron is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

## Responsible Care®

Our top priority is to provide the highest quality products and services, and to focus on the American Chemistry Council's Responsible Care® initiative and safety in all of our facilities.

## Additional Information

North America		Europe/Middle East	
U.S. & Canada:	1-888-STYRON1 1-989-633-1718	Germany:	+800 444 11 444 +32 3 450 2967 +8001811361
Mexico:	+1-800-441-4369		
Latin America		South Africa	
Argentina:	+54-11-4319-0100		+800-99-5078
Brazil:	+55-11-5188-9000		
Colombia:	+57-1-219-6000	Asia Pacific	
Mexico:	+52-55-5201-4700		+800-7776-7776 +603-7965-5392

[www.styron.com](http://www.styron.com)

This document is intended for use within Europe, Latin America, North America

Published June 2010

© 2010 Styron LLC, Styron HoldCo B.V., and subsidiaries

