

Nr. 220 din 14.02.2024

Agregat grosier, sort 16-31,5 mm

5. Determinarea granulozității

Mărima ochiurilor sitei, mm	2 D 64	1,4 D 45	D 32(31,5)	d 16	d/2 8
Valoarea admisibilă, SM SR EN 12620+A1:2010 pct. 4.3.2, tab. 2 ($D/d \leq 2$ sau $D \leq 11,2$)	100	98-100	80-99	0-20	0-5
Procent masic de trecere, %	100	100	80,00	4,32	3,17
Categorie (G^d)	$G_C 80/20$				
Valoarea admisibilă, SM SR EN 13242+A1:2010 pct. 4.3.1, tab. 2, ($d \geq 1$, $D > 2$)	100	98-100	80-99	0-20	0-5
Procent masic de trecere, %	100	100	80,00	4,32	3,17
Categorie (G)	$G_C 80-20$				

