Laboratory Test report





FORM L-54 Edition 01 - Revision 03 - Date : 20/05/2020

Mechanical impact resistance test

General information

Subject: VOLTANA EVO 1 - 16 Oslon Square Giant - Philips 75W

Asked by: SZÜGYI János Péter

<u>Created on</u>: 12/01/2021 <u>Started on</u>: 13/01/2021 <u>Test number</u>: D210050

Reference norm: IEC/EN 60598-1 & 62696 Standards

Sample(s): E210035, E210036, E210037

Folder : P-F21002

Test conditions

Luminaire: VOLTANA EVO 1

Quantity of sample under test: 5

<u>Protector Material</u> : PC

Serigraphy: None

Protector supplier: External - Gaggione

Operator : Philippe Léonard



1/4

IMG_7602

Conclusion



Success

Conclusion .

Conformity statement according to TR 62696:2011 and section 4.13 of IEC 60598-1:2014, AMD1:2017:

IK10 passed.

Validated by : Duplicate to : RACANELLI Frank, SZÜGYI János Péter, **D210050**

GHYSENS Gilles HORVÁTH Csaba, CSIKÓS Balázs, BEDŐ Péter

LAB: 15/03/2021

Test(s)

| Name | Description | Result |
|---------------|--|-------------|
| Impact points | At pendulum hammer 5 impact points distributed on protector surface One impact on each point 2 supplementary impacts on the most fragile point | Informative |
| IK08 | Impact energy: 5 joules Hammer weight: 1.7 Kg Height of fall: 30 Cm | Informative |
| IK09 | Impact energy: 10 joules Hammer weight: 5 kg Height of fall: 20 cm | Informative |
| IK10 | Impact Energy: 20 joules Hammer Weight: 5 Kg Height of fall: 40 cm | Informative |

Impact points

Annex(es)



D210050 2/4

Result(s)

| IK 08 | Impact | 1 | | | 2 | | | 3 | | | | 4 | | 5 | | |
|--------|--------|------|------------|---|------|---|---|------|---|---|------|---|---|------|------|------|
| Sample | Shot | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 |
| 1 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 2 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 3 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 4 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 5 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| | | | | | | | | | | | | | | | | |
| | | - | NOT TESTED | | | | | | | | | | | | | |

<u>IK09</u>

Result(s)

| IK 09 | Impact | 1 | | | 2 | | | 3 | | | | 4 | | 5 | | |
|--------|--------|------|-------|-------|------|---|---|------|---|---|------|---|---|------|------|------|
| Sample | Shot | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 |
| 1 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 2 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 3 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 4 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 5 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| | | | | | | | | | | | | | | | | |
| | | - | NOT T | ESTED | | | | | | | | | | | | |

<u>IK10</u>

Result(s)

| IK 10 | Impact | 1 | | | 2 | | | 3 | | | 4 | | | 5 | | |
|--------|--------|------|------------|---|------|---|---|------|---|---|------|---|---|------|------|------|
| Sample | Shot | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 | 1 | 2 | 3 |
| 1 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 2 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 3 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 4 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| 5 | | Pass | - | - | Pass | - | - | Pass | - | - | Pass | - | - | Pass | Pass | Pass |
| | | | | | · | | | | | | | | | | | |
| | | - | NOT TESTED | | · | | | | | | | | | | | |

D210050 3/4

Test room temperature (°C):

22

Measurement equipment:

Pendulum hammer with chariot (M062) Thermometer (A039/3)

Quantities measured:

For IK 04/05/06: Verification of the mechanical strength of a luminaire according to PT-S-13 For IK07/08/09/10/10+: Verification of the mechanical strength of a luminaire according to PT-S-05

Uncertainties:

Temperature: 0,6 °K

Mass: 0,25 %

Dynamometric key:

From 0.5 to 2.5 Nm : 0,15 Nm From 2.5 to 5 Nm : 0,22 Nm From 5 to 25 Nm : 0,83 Nm From 25 to 60 Nm : 2,73 Nm From 60 to 100 Nm : 3,55 Nm

For IK 04/05/06, Impact energy: ± 10% For IK07/08/09/10/10+, Impact energy: ± 1%

Decision rules:

Pass/fail criteria according to GDE-GUI-003

By visual inspection (or other means if necessary):

Luminaire shows dangerous behavior: fail Luminaire shows no dangerous behavior: pass

When several luminaires are tested, 4 out of 5 samples need to show positive result for compliance of the batch

End of accredited report:

D210050 4/4