

**Societatea cu răspundere limitată «Mezanin-V»**

CF 1003600056058 TVA: 0306747

Adresa: MD 2060, or. Chișinău, bd. Dacia 35

CD MD40FT222410300001236498 MDL BC"FinComBank"SA BIC: FTMDMD2X853

CD MD41AG000000022512042308 MDL BC"Moldova - Agroindbank"SA BIC: AGRNMD2X

tel: +373 (22) 000 333 tel/fax: +373 (22) 636 191 e-mail: [office@mezanin.md](mailto:office@mezanin.md) web: [www.mezanin.md](http://www.mezanin.md) skype: mezanin\_v**TEST REPORT**

|                             |                 |                                                                                |
|-----------------------------|-----------------|--------------------------------------------------------------------------------|
| Item                        |                 | Medical (YGPY-1B)                                                              |
| Composition                 |                 | 50% PU, 50% POLYESTER                                                          |
| Thickness                   |                 | 0.38mm                                                                         |
| Width                       |                 | 140cm                                                                          |
| Weight                      |                 | 180gsm±5%                                                                      |
| Tensile Strength<br>(N/3cm) | Warp            | ≥150N                                                                          |
|                             | Weft            | ≥130N                                                                          |
| Elongation                  | Warp            | 90%                                                                            |
|                             | Weft            | 155%                                                                           |
| Tearing Strength            | Warp            | ≥30N                                                                           |
|                             | Weft            | ≥26N                                                                           |
| Peeling Strength<br>(N/3cm) | --              | ≥46N                                                                           |
| Resistance to water         | --              | PASS                                                                           |
| Resistance to UV            | ISO 105B02      | ≥6                                                                             |
| Resistance to alcohol       | --              | PASS                                                                           |
| Anti-microbial              | ISO 22196       | PASS<br>(Escherichia coli,<br>Klebsiella pneumoniae,<br>Staphylococcus aureus) |
| Flame-retardancy            | Cigarette&match | Pass                                                                           |