

 ÇAMSAN ENTEGRE LAMINATE FLOORING QUALITY SPECIFICATIONS			
CHARACTERISTIC	STANDARD	12mm SERENZA - AC5 (EN STANDARD)	UNIT
DENSITY	ÇAMSAN ENTEGRE	920 ± %3	kg/m ³
THICKNESS OF THE ELEMENT (t)	TS EN 13329+A2	$\Delta t_{average} \leq 0,50$, $t_{max.} - t_{min.} \leq 0,50$	mm
WIDTH OF THE SURFACE LAYER (W)		$\Delta W_{average} \leq 0,10$, $\Delta l_{average} \leq 0,10$, $W_{max.} - W_{min.} \leq 0,20$, $L_{max.} - L_{min.} \leq 0,20$	mm
LENGTH OF THE SURFACE LAYER (l)		$l \leq 1500 : \Delta l \leq 0,5$ mm, $l > 1500 : \Delta l \leq 0,3$ mm/m.	mm
SQUARENESS OF THE ELEMENT (q)		$q_{max.} \leq 0,20$	mm
STRAIGHTNESS OF THE SURFACE LAYER (s)		$S_{max.} \leq 0,30$	mm / m
FLATNESS OF THE ELEMENT (f)		$f_{w, concave} \leq \% 0,15$, $f_{w, convex} \leq \% 0,20$, $f_{l, concave} \leq \% 0,50$, $f_{l, convex} \leq \% 1,00$	mm
OPENING BETWEEN ELEMENTS(O)		$O_{average} \leq 0,15$, $O_{max.} \leq 0,20$	mm
HEIGHT DIFERENCE BETWEEN ELEMENTS		$h_{average} \leq 0,10$, $h_{max.} \leq 0,15$	mm
SURFACE SOUNDNESS	TS EN 13329 / TS EN 311	AC5 $\geq 1,25$	N / mm ²
THICKNESS SWELLING	TS EN 13329	$\leq \%15$	%
HUMIDITY	TS EN 322	$\%4 \leq H \leq \%10$ $H_{max.} - H_{min.} \leq \%3$	%
FREE FORMALDEHYDE AMOUNT	TS EN 12460-3	E0: $\leq 1,75$ E1: $1,75 < x \leq 3,50$	mg / m ² . h
DIMENSIONAL VARIATIONS AFTER CHANGES IN RELATIVE HUMIDITY	TS EN 13329 / TS EN 318	$\delta l_{average} \leq 0,9$, $\delta W_{average} \leq 0,9$	mm
ABRASION RESISTANCE	TS EN 13329	AC5; ≥ 6000	Rev
SMALL-DIAMETER BALL IMPACT RESISTANCE	TS EN 17368	≥ 70 mm	N, mm
LARGE-DIAMETER BALL IMPACT RESISTANCE	TS EN 13329 / TS EN 438-2	≥ 1000 mm	
RESISTANCE TO STAINING	TS EN 438-2	5 (group 1 ve group 2), 4 (group 3)	Class
EFFECT OF A CASTOR CHAIR	TS EN 425	25.000 cycles - no damage	View
EFFECT OF A FURNITURE LEG	TS EN 424	No damage shall be visible	View
APPERANCE, SURFACE DEFECTS	TS EN 438-2	Minor surface defects as defined in the EN 438 series are permitted.	View
STATIC INDENTATION	TS EN ISO 24343-1	$\leq 0,05$	mm
LIGHT FASTNESS	TS EN 20105	Not worse than 4	Class
LOCKING RESISTANCE	ISO 24334	FI ≥ 1 kN/m Fs ≥ 2 kN/m	N / mm ²

GENEL MÜDÜRLÜK / HEAD OFFICE

Büyükdere Cad. Eski Oto Sanayi
Emektar Sok. No:4 K:2 4. Levent
Kağıthane/ İstanbul / TÜRKİYE
Tel : +90 212 284 62 43
Faks : +90 212 284 62 45

FABRİKA / FACTORY

Sakarya İl. Organize San. Bölgesi
Hendek / Sakarya / TÜRKİYE
Tel : +90 264 654 58 18
Faks : +90 264 654 58 16

www.camsan.com

www.parkelam.com

V.D. Yenikapı
V.D. NO: 228 005 3797
Mersis No: 0228005379700014