

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T

21003762-
İNG

02-21

TEST RESULT

LINT AND OTHER PARTICLES GENERATION FROM NONWOWEN;

Test Metod: ISO 9073-10: 2003 (*)

5 test samples that in cross direction are maintained to twisting and compression action with Gelbo Flex for inner and outer surface in a clean room condition (according to ISO 14644-1 Class 5).

Lint and particles detached from the sample are counted with counter device and classified to size range.

Min. measuring size of SOLAIR 3100 particles measuring device: 0,3 µm,

Max. measuring size of SOLAIR 3100 particles measuring device: 25 µm.

Air flow: 28,3 ± 1,4 L/min Working mode: 30 s x 10 consecutive periods

Critical area

SAMPLE, INNER SURFACE (3 µm - 25 µm)		SAMPLE, OUTER SURFACE (3 µm - 25 µm)	
Total linting	: 44	Total linting	: 49
Standard deviation	: 28	Standard deviation	: 11
Coefficient of variation	: 63%	Coefficient of variation	: 23%
Coefficient of linting (CL)	: 2	Coefficient of linting (CL)	: 2
SAMPLE, MATERIAL (TOTAL)			
Total linting	: 93		
Coefficient of linting (CL)*	: 2		

*According to EN ISO EN ISO 13795-1:2019, Coefficient of linting (CL) (log 10) should be ≤4 for analysis of critical product area and less critical product area of both standard performance and high performance testing.

LINT AND OTHER PARTICLES GENERATION FROM NONWOWEN;

Test Metod: ISO 9073-10: 2003 (*)

5 test samples that in cross direction are maintained to twisting and compression action with Gelbo Flex for inner and outer surface in a clean room condition (according to ISO 14644-1 Class 5).

Lint and particles detached from the sample are counted with counter device and classified to size range.

Min. measuring size of SOLAIR 3100 particles measuring device: 0,3 µm,

Max. measuring size of SOLAIR 3100 particles measuring device: 25 µm.

Air flow: 28,3 ± 1,4 L/min

Working mode: 30 s x 10 consecutive periods

Less Critical area

SAMPLE, INNER SURFACE (3 µm - 25 µm)		SAMPLE, OUTER SURFACE (3 µm - 25 µm)	
Total linting	: 22	Total linting	: 15
Standard deviation	: 15	Standard deviation	: 7
Coefficient of variation	: 66%	Coefficient of variation	: 48%
Coefficient of linting (CL)	: 1	Coefficient of linting (CL)	: 1
SAMPLE, MATERIAL (TOTAL)			
Total linting	: 37		
Coefficient of linting (CL)*	: 2		

*According to EN ISO EN ISO 13795-1:2019, Coefficient of linting (CL) (log 10) should be ≤4 for analysis of critical product area and less critical product area of both standard performance and high performance testing.

**BAĞCILAR İNŞİ CİHAZLAR
VE SAĞLIK ÜRÜNLERİ SAN. VE TİC. LTD.ŞTİ.**
Mahmutbey Mah. 2567.Sk. No:11, 21. Yeri No:11,21
Bağcılar / İSTANBUL / TÜRKİYE
Tel: 0212 445 45 25 T.C.Sic.No: 294704
Güneşli V.D.: 997 067 1442