



**STANDARD
100**

**BEWO 084394
TESTEX**

**This certificate BEWO 084394 is valid until
15.08.2026.**

SUPPORTING DOCUMENTS

- ✓ Test report : BJ015 266840.1
- ✓ Declaration of conformity in accordance with
EN ISO 17050-1 as required by OEKO-TEX®
- ✓ OEKO-TEX® Terms of Use (ToU)

Matz Bachmann
Managing Director

Janine Kuchelmeister
Ecology Team Leader




Zurich, 2025-07-24



SoftShell-350

94% POLYESTER / 6% SPANDEX + TPU

350 GSM / PLAIN 1/1



Fabric name	SoftShell-350
Fabric weight	350 ± 5 gsm
Composition	94% Polyester, 6% Spandex +TPU
Full width	150 ± 2 cm
Weave	Plain 1/1
Fabric Finishes	-
Area of use	work and outdoor clothing
Washing instruction	

Physical properties*

			warp	weft
1	Tensile strength, N	ISO 13934-1:2013	-	-
2	Tearing strength, N	ISO 13937-3:2000	-	-
3	Dimensional Stability To Washing, max.	ISO 6330:2000	5.0%	5.0%
4	Abrasion Resistance	ISO 12947-2:2002	-	
5	Pilling Resistance (after 1000 rev.)	ISO 12945-2:2000	N/A	
6	Colour Fastness To Washing (cotton+polyester) 60°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	4	
	Colour staining	ISO 105-C06:2010	N/A	
7	Colour Fastness To Perspiration, min.	ISO 105-E04:2013		
	Colour change		N/A	
	Colour staining		N/A	
8	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4	
	Wet		4	
9	Colour Fastness To Light	ISO 105-B02:2013	N/A	

* The values shown are indicative and may vary slightly from batch to batch.

* N/A - not applicable.

www.xmtextiles.com

XM TEXTILES EUROPE

Dariaus ir Gireno st. 42A, Room 509

Vilnius, LT-02189, Lithuania

Tel. +370 52 078 703

info@xmtextiles.com






Polar Fleece-180

100% POLYESTER

180 GSM / KNITTED



Fabric name	Polar Fleece-180
Fabric weight	180 ± 5 gsm
Composition	100% polyester
Full width	150 ± 2 cm
Weave	knitted
Finishes	antipilling
Application	workwear jackets or sport vests
Washing instruction	

Physical properties*

			warp	weft
1	Dimensional Stability To Washing, max.	ISO 6330:2000	3.0%	3.0%
2	Abrasion Resistance	ISO 12947-2:2002	> 20 000	
3	Pilling Resistance, as received /after 2000 rubs	ISO 12945-2:2000	4	
4	Colour Fastness To Washing (cotton+polyester) 40°C, min.	ISO 105-C06:2010		
	Colour change	ISO 105-C06:2010	3-4	
5	Colour Fastness To Drycleaning, min.	ISO 105-D01:2010	4-5	
6	Colour Fastness To Rubbing, min.	ISO 105-X12:2001		
	Dry		4	
	Wet		4-5	
7	Colour Fastness To Organic Solvents	ISO 105-X05:1994	4-5	
8	Colour Fastness To Light	ISO 105-B02:2013	> 4	

* The values shown are indicative and may vary slightly from batch to batch.



XM TEXTILES EUROPE

Dariaus ir Gireno st. 42A, Room 509
Vilnius, LT-02189, Lithuania
Tel. +370 52 078 703
info@xmtextiles.com