



Sialkot Material Testing Laboratory

UNIT ESTABLISHED BY TRADE DEVELOPMENT AUTHORITY OF PAKISTAN MINISTRY OF COMMERCE GOVT OF PAKISTAN

NEAR SUBLIME CHOWK, MARALA ROAD, SIALKOT - 51310-PAKISTAN

TEL: 0092-52-3562818 simtelstlab@gmail.com FAX: 0092-52-3554217



Ref. No. PM/SIMTEL/22/255

September 13, 2022

HARDNESS / TEST REPORT

In Respect of : M/s. Care & Cure Surgico Sialkot
Sample Received from : Representative
Name of Samples : Surgical Instruments
Hardness (Average) : HRC (Rockwell Hardness Tester)

Results:

Rockwell Hardness of instruments average is 52 to 56 HRC

This analytical /test report is based solely on the particular sample(s) supplied by the party and should not be reproduced in part.

Sampling has not been performed by the SIMTEL and the SIMTEL does not accept responsibility that samples(s) supplied is/are truly representative samples(s) of any batch or stock or entire production.

While the SIMTEL agrees to take every reasonable precaution to ensure validity of its test results, it assumes no liability for the accuracy thereof beyond the amount of the fee charged for the analysis/test.

The party shall assume full responsibility for the ethical use of the results in the analysis/test reports and the laboratory shall be held free from any and all claims, which may result from the use of such data by the party or others.

After completion of the report the sample will be preserved for three month until negotiated otherwise.



Engr. Amjad Hussain
Project Director