

# LATEX

## Comfort-fit

### Powder-free Examination Gloves



Recommended  
for medical use



- Ideal glove thickness for vigorous procedures
- Cost saving alternative for supporting medical team
- Exceptional elongation & dexterity
- Snug fit ability
- Strong grip
- Renewable resource - natural rubber latex material
- Chemical resistant
- Recyclable packaging

## PS54

Reference code: IMPS54Y

### PRODUCT SPECIFICATION (ASTM D6319 & EN 455)

Colour: Natural colour

| Dimension (mm) | Spec      | Typical   |     |
|----------------|-----------|-----------|-----|
|                |           | mm        | mil |
| Cuff           | Min. 0.04 | 0.05      | 2.0 |
| Palm           | Min. 0.05 | 0.06      | 2.4 |
| Finger         | Min. 0.06 | 0.08      | 3.1 |
| Length         | Min. 240  | 240 - 245 |     |

### Physical Properties

#### Unaged

|                        |          |           |
|------------------------|----------|-----------|
| Tensile strength (MPa) | Min. 18  | 28 - 32   |
| Elongation (%)         | Min. 500 | 500 - 540 |
| Force at break (N)     | Min. 6.0 | 6.0 - 6.3 |

#### Aged

|                        |          |           |
|------------------------|----------|-----------|
| Tensile strength (MPa) | Min. 14  | 29 - 33   |
| Elongation (%)         | Min. 400 | 460 - 500 |
| Force at break (N)     | Min. 6.0 | 6.0 - 6.3 |

### PACKAGING INFORMATION

|                     |                                  |
|---------------------|----------------------------------|
| Case dimension (mm) | 365 x 250 x 250                  |
| Box dimension (mm)  | 240 x 120 x 70                   |
| Packing mode        | 100 pcs / box, 10 boxes / carton |

|                 |              |              |              |
|-----------------|--------------|--------------|--------------|
| Maximum loading | 20'GP        | 40'GP        | 40'HQ        |
|                 | 1215 cartons | 2600 cartons | 3000 cartons |

### PRODUCT ATTRIBUTES

Medical • Polymer coated • Smooth surface • Standard cuff 9.5" • AQL 1.5



# iNtouch™

# NITRILE

## Shield-aid

### Powder-free Examination Gloves



Recommended  
for medical use



- Cost saving alternative for supporting medical team
- Excellent film strength
- Excellent puncture resistance
- Customised fitting property, prevent hand fatigue
- Clear indication of tears and breaks
- Prevent type I hypersensitivity
- Chemical resistant
- Recyclable packaging

### CS30

Reference code: IMCS30

#### PRODUCT SPECIFICATION (ASTM D6319 & EN 455)

Colour: Natural colour, blue

| Dimension (mm) | Spec      | Typical   |     |
|----------------|-----------|-----------|-----|
|                |           | mm        | mil |
| Cuff           | Min. 0.04 | 0.05      | 2.0 |
| Palm           | Min. 0.05 | 0.06      | 2.4 |
| Finger         | Min. 0.06 | 0.08      | 3.1 |
| Length         | Min. 240  | 240 - 245 |     |

| Physical Properties    |          | Unaged    |  |
|------------------------|----------|-----------|--|
| Tensile strength (MPa) | Min. 18  | 28 - 32   |  |
| Elongation (%)         | Min. 500 | 500 - 540 |  |
| Force at break (N)     | Min. 6.0 | 6.0 - 6.3 |  |
|                        |          | Aged      |  |
| Tensile strength (MPa) | Min. 14  | 29 - 33   |  |
| Elongation (%)         | Min. 400 | 460 - 500 |  |
| Force at break (N)     | Min. 6.0 | 6.0 - 6.3 |  |

#### PACKAGING INFORMATION

|                     |                                  |
|---------------------|----------------------------------|
| Case dimension (mm) | 250 x 240 x 245                  |
| Box dimension (mm)  | 240 x 120 x 45                   |
| Packing mode        | 100 pcs / box, 10 boxes / carton |

|                 |              |              |              |
|-----------------|--------------|--------------|--------------|
| Maximum loading | 20'GP        | 40'GP        | 40'HQ        |
|                 | 1860 cartons | 3960 cartons | 4410 cartons |

#### PRODUCT ATTRIBUTES

Medical • Chlorinated • Fingertips textured • Standard cuff 9.5" • AQL 1.5



# iNtouch™

|   |                                |         |        |
|---|--------------------------------|---------|--------|
| <br><b>KOSSAN</b><br><small>STRETCHING LIMITS • SINCE 1979</small> | <h1>PRODUCT SPECIFICATION</h1> | Doc No  |        |
|   |                                | PS-0003 |        |
|   |                                | Rev     | Page   |
|   |                                | 2       | 2 of 2 |

Product : Non-Sterile, Ambidextrous, Finger-Textured Surface, Powder Free Nitrile Examination Gloves

Color : White, Blue, Black

Product Code : OCPFNF-BF-3.0 (EB53001JA-BF), OCPFNF-WC-3.0 (EB53002JA-WC), OCPFNF-BT-3.0 (EB53002JA-BT), OCPFNF-KB-3.0 (EB53001JA-KB)

Reference Code : CS30-BF, CS30-WC, CS30-BT, CS30-KB

Grade : AQL 1.5

Inspection Method : ASTM D6319 and EN 455-1/2/3 (Current Version)

Quality Assurance : Manufactured under ISO 13485, CAN/CSA ISO 13485, ISO 9001 and US FDA QSR Quality Management System

| No        | Test                     | Particular  | Specification            | In-house Inspection Level / AQL |                          |
|-----------|--------------------------|---|--------------------------|---------------------------------|--------------------------|
| 1         | Dimension (mm)           | Width   | Extra Small              | 75 ± 5                          | S2/AQL 4.0               |
|           |                          |   | Small                    | 85 ± 5                          |                          |
|           |                          |   | Medium                   | 95 ± 5                          |                          |
|           |                          |   | Large                    | 106 ± 5                         |                          |
|           |                          |   | Extra Large              | 116 ± 5                         |                          |
|           |                          |   | Extra Extra Large        | 125 ± 5                         |                          |
|           |                          | Length  | Min. 240                 |                                 |                          |
|           |                          | Thickness (Single Wall)   | Cuff (25 ± 5 from bead)  | Min. 0.04                       |                          |
|           | Palm (center of palm)    | Min. 0.05   |                          |                                 |                          |
|           | Finger (13 ± 3 from tip) | Min. 0.06   |                          |                                 |                          |
| 2         | Physical Properties      | Unaged (ASTM)   | Tensile Strength (MPa)   | Min. 18                         | S2/AQL 4.0               |
|           |                          |   | Elongation at Break (%)  | Min. 500                        |                          |
|           |                          | Unaged (EN)   | Force at Break (N)       | Min. 6.0                        | n = 13<br>(Median Value) |
|           |                          | Aged (ASTM)   | Tensile Strength (MPa)   | Min. 14                         | S2/AQL 4.0               |
|           |                          |   | Elongation at Break (%)  | Min. 400                        |                          |
| Aged (EN) | Force at Break (N)       | Min. 6.0  | n = 13<br>(Median Value) |                                 |                          |
| 3         | Freedom from Holes       |   |                          | GI/AQL 1.5                      |                          |
| 4         | Visual Defects (Major)   | Crack Line, Deformed Gloves, Dirt/Stain ≥1mm <sup>2</sup> , Discoloration, Flow Mark, Incomplete Beading, Lump ≥2mm <sup>2</sup> , Mix Size, Mix Type, Powder Mark, Polymer Mark, Sticky Gloves/Sticky Pleat ≥5mm, Thin Spot/Fish Eye |                          | GI/AQL 2.5                      |                          |
| 5         | Visual Defects (Minor)   | Blister, Dirt/Stain <1mm <sup>2</sup> , Lump <2mm <sup>2</sup> , Poor Beading, Sticky Pleat <5mm  |                          | GI/AQL 4.0                      |                          |
| 6         | Powder Residue           | Max 1.5 mg/glove  |                          | n = 5                           |                          |

Distribution or copying of this document is prohibited without the prior permission of KISB

|   |                                |         |        |
|---|--------------------------------|---------|--------|
|  | <h1>PRODUCT SPECIFICATION</h1> | Doc No  |        |
|   |                                | PS-1025 |        |
|   |                                | Rev     | Page   |
|   |                                | 1       | 2 of 2 |

Product : Non-Sterile, Ambidextrous, Smooth Surface, Powder Free Polymer Coated, Natural Rubber Latex Examination Gloves

Color : Natural

Product Code : OLPYS-NA-5.4 (ER35401AA-NA)

Reference Code : PS54Y

Grade : AQL 1.5

Inspection Method : ASTM D3578 and EN 455-1/2/3 (Current Version)

Quality Assurance : Manufactured under ISO 13485, CAN/CSA ISO 13485, ISO 9001 and US FDA QSR Quality Management System

| No                       | Test                   | Particular  | Specification            | In-house Inspection Level / AQL |                          |
|--------------------------|------------------------|---|--------------------------|---------------------------------|--------------------------|
| 1                        | Dimension (mm)         | Width   | Extra Small              | 75 ± 5                          | S2/AQL 4.0               |
|                          |                        |   | Small                    | 85 ± 5                          |                          |
|                          |                        |   | Medium                   | 95 ± 5                          |                          |
|                          |                        |   | Large                    | 106 ± 5                         |                          |
|                          |                        |   | Extra Large              | 116 ± 5                         |                          |
|                          |                        |   | Extra Extra Large        | 125 ± 5                         |                          |
|                          |                        | Length  | Min. 240                 |                                 |                          |
|                          |                        | Thickness (Single Wall)   | Cuff (25 ± 5 from bead)  | Min. 0.06                       |                          |
| Palm (center of palm)    | Min. 0.08              |   |                          |                                 |                          |
| Finger (13 ± 3 from tip) | Min. 0.10              |   |                          |                                 |                          |
| 2                        | Physical Properties    | Unaged (ASTM)   | Tensile Strength (MPa)   | Min. 18                         | S2/AQL 4.0               |
|                          |                        |   | Elongation at Break (%)  | Min. 650                        |                          |
|                          |                        | Unaged (EN)   | Force at Break (N)       | Min. 6.0                        | n = 13<br>(Median Value) |
|                          |                        |   | Aged (ASTM)              | Tensile Strength (MPa)          | Min. 14                  |
|                          |                        | Elongation at Break (%)   |                          | Min. 500                        |                          |
| Aged (EN)                | Force at Break (N)     | Min. 6.0  | n = 13<br>(Median Value) |                                 |                          |
| 3                        | Freedom from Holes     |   |                          | GI/AQL 1.5                      |                          |
| 4                        | Visual Defects (Major) | Crack Line, Deformed Gloves, Dirt/Stain ≥1mm <sup>2</sup> , Discoloration, Flow Mark, Incomplete Beading, Lump ≥2mm <sup>2</sup> , Mix Size, Mix Type, Powder Mark, Polymer Mark, Sticky Gloves/Sticky Pleat ≥5mm, Thin Spot/Fish Eye |                          | GI/AQL 2.5                      |                          |
| 5                        | Visual Defects (Minor) | Blister, Dirt/Stain <1mm <sup>2</sup> , Lump <2mm <sup>2</sup> , Poor Beading, Sticky Pleat <5mm  |                          | GI/AQL 4.0                      |                          |
| 6                        | Powder Residue         | Max 1.5 mg/glove  |                          | n = 5                           |                          |
| 7                        | Protein                | Max 50 µg/g (for EN Testing Method)   |                          | n = 8                           |                          |
|                          |                        | Max 50 µg/dm <sup>2</sup> (for ASTM Testing Method)   |                          | n = 3                           |                          |

Distribution or copying of this document is prohibited without the prior permission of KISB

Digitally signed by Dicusar Vladimir  
Date: 2022.09.21 17:19:41 EEST  
Reason: MoldSign Signature  
Location: Moldova



• Powder-free Examination Gloves  
• Chemical permeation tested • Viral penetration tested • Fentanyl tested  
• Chemotherapy drugs tested

**NITRILE**  
*Shield-aid*

**XS**  
5 - 6  
100 gloves  
by weight


**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

**NITRILE**

*Shield-aid*

**CS30**

Powder-free Examination Gloves



**BLUE**  
**XS**  
5 - 6  
100 gloves  
by weight



Recommended for medical use

**BLUE**  
**XS**  
5 - 6  
100 gloves  
by weight

**BLUE**  
**XS**  
5 - 6  
100 gloves  
by weight

**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

**XS**

**NITRILE**

*Shield-aid*

Powder-free Examination Gloves

- Gants d'examen nitrile sans poudre
- Puderfrei untersuchungshandschuhe aus nitril
- Mănuși nitril nepudrate pentru examinare

**XS**  
5 - 6  
100 gloves  
by weight

**XS**

**NITRILE**

*Shield-aid*

Powder-free Examination Gloves

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PFN

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0521), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants. Gloves used for protection against chemotherapy drugs exposure should be selected specifically for the type of drugs being used. Users are advised to review Material Safety Data Sheets for the chemicals being used to determine the required level of protection.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** (2731784M) Tel +603 3392 3013  
Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3<sup>rd</sup>, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.mt](mailto:info@advena.mt)  
Tower Business Centre, 2nd Floor, Tower Street, Swatar, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia



9555256614712

REF  
IMCS30BF-XS



Tested for use with chemotherapy drugs using ASTM D6978.

| Chemotherapy drugs & chemicals   | Breakthrough detection time |
|--|-----------------------------|
| Cisplatin 1 mg/ml, Cyclophosphamide (Cytoxan) 20 mg/ml, Cytarabine 100 mg/ml, Docetaxel (Taxot) 10 mg/ml, Doxorubicin hydrochloride 2 mg/ml, Etoposide 20 mg/ml, Fluorouracil 50 mg/ml, Ifosfamide 50 mg/ml, Methotrexate 25 mg/ml, Mitomycin C 0.5 mg/ml, Mitoxantrone 2 mg/ml, Paclitaxel (Taxol) 6 mg/ml, Vincristine sulfate 1 mg/ml | Minimum 240 min             |
| Thiotepa 10 mg/ml  | 30.2 min                    |
| Carmustine (BCNU) 3.3 mg/ml  | 10.1 min                    |
| Fentanyl citrate injection (100 µg/2ml)  | Minimum 240 min             |

Warning: Not recommended for use with Carmustine and Thiotepa.

| Chemicals                     | Level | Mean degradation | Chemicals                  | Level | Mean degradation |
|-------------------------------|-------|------------------|----------------------------|-------|------------------|
| *4% Chlorhexidine Digluconate | 6     | 19.0%            | 10% Sodium Percarbonate    | 6     | 15.4%            |
| 40% Sodium Hydroxide (K)      | 6     | 42.9%            | 10% Acetic Acid            | 4     | 66.7%            |
| 10-13% Sodium Hypochlorite    | 6     | 14.7%            | 37% Formaldehyde (T)       | 3     | 5.0%             |
| 50% Sulphuric Acid            | 6     | 20.5%            | 30% Hydrogen Peroxide (P)  | 2     | 22.8%            |
| 5% Ethidium Bromide           | 6     | 3.4%             | 25% Ammonium Hydroxide (O) | 0     | -52.0%           |
| 50% Glutaraldehyde            | 6     | 27.4%            | 65% Nitric Acid (M)        | 0     | 97.6%            |
| 0.1% Phenol                   | 6     | 33.8%            | 70% Isopropanol            | 0     | 62.2%            |
| 1.5% Methanol in Water        | 6     | 21.9%            | 35% Ethanol                | 0     | 38.8%            |
| 3% Povidone-iodine            | 6     | 33.7%            | 99% Acetic Acid (N)        | 0     | 93.9%            |


\* Permeation rate 7 µg/cm<sup>2</sup>/min

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1: 2016 +A1: 2018.  
Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min

LOT



235 x 120 x 45



• Chemotherapy drugs tested  
 • Viral penetration tested  
 • Fentanyl tested  
 • Chemical permeation tested  
 • Powder-free Examination Gloves


**NITRILE**  
*Shield-aid*

**S**  
 6-7  
 100 gloves  
 by weight

**NITRILE**  
*Shield-aid*

**CS30**

**Powder-free Examination Gloves**



Recommended for medical use



**S**  
 6-7  
 100 gloves  
 by weight

**NITRILE LD**  
*Shield-aid*  
 Powder-free Examination Gloves

**S**  
 6-7  
 100 gloves  
 by weight

**S**  
 6-7  
 100 gloves  
 by weight

**NITRILE LD**  
*Shield-aid*  
 Powder-free Examination Gloves

**S**

**NITRILE**  
*Shield-aid*

**Powder-free Examination Gloves**

- Gants d'examen nitrile sans poudre
- Puderfrei untersuchungshandschuhe aus nitril
- Mănuși nitril nepudrate pentru examinare

**S**  
 6-7  
 100 gloves  
 by weight

**S**

**NITRILE**  
*Shield-aid*

**Powder-free Examination Gloves**

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PFN

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0521), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants. Gloves used for protection against chemotherapy drugs exposure should be selected specifically for the type of drugs being used. Users are advised to review Material Safety Data Sheets for the chemicals being used to determine the required level of protection.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** (2731784M) Tel +603 3392 3013  
 Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3<sup>rd</sup>, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.com](mailto:info@advena.com)  
 Tower Business Centre, 2nd Floor, Tower Street, Swatara, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
 Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia



**REF**  
**IMCS30BF-S**



**Tested for use with chemotherapy drugs using ASTM D6978.**

| Chemotherapy drugs & chemicals  | Breakthrough detection time |
|---|-----------------------------|
| Cisplatin 1 mg/ml, Cyclophosphamide (Cytoxan) 20 mg/ml, Cytarabine 100 mg/ml, Dacarbazine (DTIC) 10 mg/ml, Doxorubicin hydrochloride 2 mg/ml, Etoposide 20 mg/ml, Fluorouracil 50 mg/ml, Ifosfamide 50 mg/ml, Methotrexate 25 mg/ml, Mitomycin C 0.5 mg/ml, Mitoxantrone 2 mg/ml, Paclitaxel (Taxol) 6 mg/ml, Vincristine sulfate 1 mg/ml | Minimum 240 min             |
| Thiotepa 10 mg/ml   | 30.2 min                    |
| Carmustine (BCNU) 3.3 mg/ml   | 10.1 min                    |
| Fentanyl citrate injection (100 µg/2ml)   | Minimum 240 min             |

**Warning: Not recommended for use with Carmustine and Thiotepa.**


| Chemicals                     | Level | Mean degradation | Chemicals                  | Level | Mean degradation |
|-------------------------------|-------|------------------|----------------------------|-------|------------------|
| *4% Chlorhexidine Digluconate | 6     | 19.0%            | 10% Sodium Percarbonate    | 6     | 15.4%            |
| 40% Sodium Hydroxide (K)      | 6     | -42.9%           | 10% Acetic Acid            | 4     | 66.7%            |
| 10-13% Sodium Hypochlorite    | 6     | 14.7%            | 37% Formaldehyde (T)       | 3     | 5.0%             |
| 50% Sulphuric Acid            | 6     | -20.5%           | 30% Hydrogen Peroxide (P)  | 2     | 22.8%            |
| 5% Ethidium Bromide           | 6     | 3.4%             | 25% Ammonium Hydroxide (O) | 0     | -52.0%           |
| 50% Glutaraldehyde            | 6     | 27.4%            | 65% Nitric Acid (M)        | 0     | 97.6%            |
| 0.1% Phenol                   | 6     | 33.8%            | 70% Isopropanol            | 0     | 62.2%            |
| 1.5% Methanol in Water        | 6     | 21.9%            | 35% Ethanol                | 0     | 38.8%            |
| 3% Povidone-iodine            | 6     | 33.7%            | 99% Acetic Acid (N)        | 0     | 93.9%            |

\* Permeation rate 7 µg/cm<sup>2</sup>/min

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1: 2016 +A1: 2018.  
 Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
 Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min



235 x 120 x 45



• Chemotherapy drugs tested  
• Viral penetration tested  
• Fentanyl tested


**NITRILE**

**NITRILE**

*Shield-aid*

**CS30**

**Powder-free Examination Gloves**



**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

**BLUE**  
M  
7-8  
100 gloves by weight



Recommended for medical use



**BLUE**  
M  
7-8  
100 gloves by weight

**BLUE**  
M  
7-8  
100 gloves by weight

**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

**M**

**NITRILE**

*Shield-aid*

**Powder-free Examination Gloves**

- Gants d'examen nitrile sans poudre
- Puderfrei untersuchungshandschuhe aus nitril
- Mănuși nitril nepudrate pentru examinare

**M**  
7-8  
100 gloves by weight

**M**

**NITRILE**

*Shield-aid*

**Powder-free Examination Gloves**

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PFN

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0521), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants. Gloves used for protection against chemotherapy drugs exposure should be selected specifically for the type of drugs being used. Users are advised to review Material Safety Data Sheets for the chemicals being used to determine the required level of protection.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** (2731784M) Tel +603 3392 3013  
Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3<sup>rd</sup>, Jalan Kapar, 42100 Klang, Selangor, Malaysia.


**ADVENA LIMITED** Email [info@advena.com](mailto:info@advena.com)  
Tower Business Centre, 2nd Floor, Tower Street, Swatara, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia



**REF**  
IMCS30BF-M



Tested for use with chemotherapy drugs using ASTM D6978.

| Chemotherapy drugs & chemicals  | Breakthrough detection time |
|---|-----------------------------|
| Cisplatin 1 mg/ml, Cyclophosphamide (Cytoxan) 20 mg/ml, Cytarabine 100 mg/ml, Dacarbazine (DTIC) 10 mg/ml, Doxorubicin hydrochloride 2 mg/ml, Etoposide 20 mg/ml, Fluorouracil 50 mg/ml, Ifosfamide 50 mg/ml, Methotrexate 25 mg/ml, Mitomycin C 0.5 mg/ml, Mitoxantrone 2 mg/ml, Paclitaxel (Taxol) 6 mg/ml, Vincristine sulfate 1 mg/ml | Minimum 240 min             |
| Thiotepa 10 mg/ml   | 30.2 min                    |
| Carmustine (BCNU) 3.3 mg/ml   | 10.1 min                    |
| Fentanyl citrate injection (100 µg/2ml)   | Minimum 240 min             |

Warning: Not recommended for use with Carmustine and Thiotepa.

| Chemicals                     | Level | Mean degradation | Chemicals                  | Level | Mean degradation |
|-------------------------------|-------|------------------|----------------------------|-------|------------------|
| *4% Chlorhexidine Digluconate | 6     | 19.0%            | 10% Sodium Percarbonate    | 6     | 15.4%            |
| 40% Sodium Hydroxide (K)      | 6     | -42.9%           | 10% Acetic Acid            | 4     | 66.7%            |
| 10-13% Sodium Hypochlorite    | 6     | 14.7%            | 37% Formaldehyde (T)       | 3     | 5.0%             |
| 50% Sulphuric Acid            | 6     | -20.5%           | 30% Hydrogen Peroxide (P)  | 2     | 22.8%            |
| 5% Ethidium Bromide           | 6     | 3.4%             | 25% Ammonium Hydroxide (O) | 0     | -52.0%           |
| 50% Glutaraldehyde            | 6     | 27.4%            | 65% Nitric Acid (M)        | 0     | 97.6%            |
| 0.1% Phenol                   | 6     | 33.8%            | 70% Isopropanol            | 0     | 62.2%            |
| 1.5% Methanol in Water        | 6     | 21.9%            | 35% Ethanol                | 0     | 38.8%            |
| 3% Povidone-iodine            | 6     | 33.7%            | 99% Acetic Acid (N)        | 0     | 93.9%            |

\* Permeation rate 7 µg/cm<sup>2</sup>/min

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1: 2016 +A1: 2018.  
Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min



235 x 120 x 45

• Chemotherapy drugs tested • Viral penetration tested • Fentanyl tested • Powder-free Examination Gloves

**NITRILE**

*Shield-aid*

100 gloves  
by weight  
6 - 8

**NITRILE**  
*Shield-aid*

**CS30**

**Powder-free Examination Gloves**


100 gloves  
by weight  
8 - 9  
**BLUE**

**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

**BLUE**  
100 gloves  
by weight  
8 - 9



Recommended for medical use



**BLUE**  
100 gloves  
by weight  
8 - 9

**intouch**<sup>TM</sup>

**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

100 gloves  
by weight  
8 - 9

**NITRILE**  
*Shield-aid*

**Powder-free Examination Gloves**

- Gants d'examen nitrile sans poudre
- Puderfrei untersuchun gshandschuhe aus nitril
- Mănuși nitril nepudrate pentru examinare

**NITRILE**  
*Shield-aid*

**Powder-free Examination Gloves**

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PFN

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0521), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants. Gloves used for protection against chemotherapy drugs exposure should be selected specifically for the type of drugs being used. Users are advise to review Material Safety Data Sheets for the chemicals being used to determine the required level of protection.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** (2731784M) Tel +603 3392 3013  
Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3<sup>rd</sup>, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.com](mailto:info@advena.com)  
Tower Business Centre, 2nd Floor, Tower Street, Swatar, BKR 4013, Malta.


**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia



9555256614743

**REF**  
IMCS30BF-L



Tested for use with chemotherapy drugs using ASTM D6978.

| Chemotherapy drugs & chemicals  | Breakthrough detection time |
|---|-----------------------------|
| Cisplatin 1 mg/ml, Cyclophosphamide (Cytoxan) 20 mg/ml, Cytarabine 100 mg/ml, Dacarbazine (DTIC) 10 mg/ml, Doxorubicin hydrochloride 2 mg/ml, Etoposide 20 mg/ml, Fluorouracil 50 mg/ml, Ifosfamide 50 mg/ml, Methotrexate 25 mg/ml, Mitomycin C 0.5 mg/ml, Mitoxantrone 2 mg/ml, Paclitaxel (Taxol) 6 mg/ml, Vincristine sulfate 1 mg/ml | Minimum 240 min             |
| Thiotepa 10 mg/ml   | 30.2 min                    |
| Carmustine (BCNU) 3.3 mg/ml   | 10.1 min                    |
| Fentanyl citrate injection (100 µg/2ml)   | Minimum 240 min             |

Warning: Not recommended for use with Carmustine and Thiotepa.

| Chemicals                     | Level | Mean degradation | Chemicals                  | Level | Mean degradation |
|-------------------------------|-------|------------------|----------------------------|-------|------------------|
| *4% Chlorhexidine Digluconate | 6     | 19.0%            | 10% Sodium Percarbonate    | 6     | 15.4%            |
| 40% Sodium Hydroxide (K)      | 6     | -42.9%           | 10% Acetic Acid            | 4     | 66.7%            |
| 10-13% Sodium Hypochlorite    | 6     | 14.7%            | 37% Formaldehyde (T)       | 3     | 5.0%             |
| 50% Sulphuric Acid            | 6     | -20.5%           | 30% Hydrogen Peroxide (P)  | 2     | 22.8%            |
| 5% Ethidium Bromide           | 6     | 3.4%             | 25% Ammonium Hydroxide (O) | 0     | -52.0%           |
| 50% Glutaraldehyde            | 6     | 27.4%            | 65% Nitric Acid (M)        | 0     | 97.6%            |
| 0.1% Phenol                   | 6     | 33.8%            | 70% Isopropanol            | 0     | 62.2%            |
| 1.5% Methanol in Water        | 6     | 21.9%            | 35% Ethanol                | 0     | 38.8%            |
| 3% Povidone-iodine            | 6     | 33.7%            | 99% Acetic Acid (N)        | 0     | 93.9%            |

\* Permeation rate 7µg/cm<sup>2</sup>/min

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1:2016 +A1:2018  
Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min

LOT



235 x 120 x 45



• Chemotherapy drugs tested  
• Viral penetration tested • Fentanyl tested  
• Powder-free Examination Gloves


**NITRILE**  
*Shield-aid*

**XL**  
9 - 10  
100 gloves  
by weight

**NITRILE**  
*Shield-aid*

**CS30**

**Powder-free Examination Gloves**



**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

**XL**  
9 - 10  
100 gloves  
by weight

**XL**  
9 - 10  
100 gloves  
by weight

**NITRILE LD**  
*Shield-aid*  
Powder-free Examination Gloves

**intouch**<sup>TM</sup>

**XL**  
9 - 10  
100 gloves  
by weight

**XL**

**NITRILE**  
*Shield-aid*

**Powder-free Examination Gloves**

- Gants d'examen nitrile sans poudre
- Puderfrei untersuchungshandschuhe aus nitril
- Mănuși nitril nepudrate pentru examinare

**NITRILE**  
*Shield-aid*

**Powder-free Examination Gloves**

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PFN

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0521), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants. Gloves used for protection against chemotherapy drugs exposure should be selected specifically for the type of drugs being used. Users are advised to review Material Safety Data Sheets for the chemicals being used to determine the required level of protection.

User information sheet is enclosed in this package.

Made in Malaysia

**KOSSAN INTERNATIONAL SDN. BHD.** (2731784M) Tel +603 3392 3013  
Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3<sup>rd</sup>, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.com](mailto:info@advena.com)  
Tower Business Centre, 2nd Floor, Tower Street, Swatar, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.



**REF**  
IMCS30BF-XL



**Tested for use with chemotherapy drugs using ASTM D6978.**

| Chemotherapy drugs & chemicals  | Breakthrough detection time |
|---|-----------------------------|
| Cisplatin 1 mg/ml, Cyclophosphamide (Cytoxan) 20 mg/ml, Cytarabine 100 mg/ml, Dacarbazine (DTIC) 10 mg/ml, Doxorubicin hydrochloride 2 mg/ml, Etoposide 20 mg/ml, Fluorouracil 50 mg/ml, Ifosfamide 50 mg/ml, Methotrexate 25 mg/ml, Mitomycin C 0.5 mg/ml, Mitoxantrone 2 mg/ml, Paclitaxel (Taxol) 6 mg/ml, Vincristine sulfate 1 mg/ml | Minimum 240 min             |
| Thiotepa 10 mg/ml   | 30.2 min                    |
| Carmustine (BCNU) 3.3 mg/ml   | 10.1 min                    |
| Fentanyl citrate injection (100 µg/2ml)   | Minimum 240 min             |

**Warning: Not recommended for use with Carmustine and Thiotepa.**

| Chemicals                     | Level | Mean degradation | Chemicals                  | Level | Mean degradation |
|-------------------------------|-------|------------------|----------------------------|-------|------------------|
| *4% Chlorhexidine Digluconate | 6     | 19.0%            | 10% Sodium Percarbonate    | 6     | 15.4%            |
| 40% Sodium Hydroxide (K)      | 6     | -42.9%           | 10% Acetic Acid            | 4     | 66.7%            |
| 10-13% Sodium Hypochlorite    | 6     | 14.7%            | 37% Formaldehyde (T)       | 3     | 5.0%             |
| 50% Sulphuric Acid            | 6     | -20.5%           | 30% Hydrogen Peroxide (P)  | 2     | 22.8%            |
| 5% Ethidium Bromide           | 6     | 3.4%             | 25% Ammonium Hydroxide (O) | 0     | -52.0%           |
| 50% Glutaraldehyde            | 6     | 27.4%            | 65% Nitric Acid (M)        | 0     | 97.6%            |
| 0.1% Phenol                   | 6     | 33.8%            | 70% Isopropanol            | 0     | 62.2%            |
| 1.5% Methanol in Water        | 6     | 21.9%            | 35% Ethanol                | 0     | 38.8%            |
| 3% Povidone-iodine            | 6     | 33.7%            | 99% Acetic Acid (N)        | 0     | 93.9%            |

\* Permeation rate 7µg/cm<sup>2</sup>/min

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1:2016 +A1:2018  
Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min



235 x 120 x 45

# intouch™

## POWDER FREE NITRILE EXAMINATION GLOVES

EN : USER INFORMATION  
FR : INFORMATIONS DE L'UTILISATEUR  
RO : INFORMAȚII UTILIZATOR

### Available Size

XS  
S  
M  
L  
XL

ISO 374-1/Type B

ISO 374-5:2016



### EN POWDER FREE NITRILE EXAMINATION GLOVES

• Non sterile • Single Use  
• Recommended for medical use

Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III) • Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) • EU Notified Body for (Module B) and Module C2: SATRA Technology Europe Limited (2777) • UK Approved Body for (Module B) and Module C2: SATRA Technology Center Limited (A80321) • EU Declaration of Conformity & UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). This information does not reflect the actual duration of protection in the workplace and the differentiation between mixtures and pure chemicals. • The chemical resistance has been assessed under laboratory conditions from samples taken from the palm only (except in cases where the glove is equal to or over 400mm – where the cuff is tested also) and relates only to the chemical tested. It can be different if the chemical used in a mixture. • It is recommended to check that the gloves are suitable for the intended use because the conditions at the workplace may differ from the type test depending on temperature, abrasion and degradation. • When used, protective glove may provide less resistance to the dangerous chemical due to changes in physical properties. Movements, snagging, rubbing, degradation caused by chemical contact etc may reduce the actual use time significantly. For corrosive chemicals, degradation can be the most important factor to consider in selection of chemical resistant gloves. • Before usage, inspect the gloves for any defect or imperfections. • EN ISO 374-4:2019 Degradation levels indicate the change in puncture resistance of the gloves after exposure to the challenge chemical. • The penetration resistance has been assessed under laboratory conditions and relates only to the tested specimens. • Donning – Hold glove by the bead with one hand. Align the glove thumb with your other hand thumb and slide your hand into the glove, one finger into each glove finger. Pull by the glove palm to get a good fit. Don the other glove by the same procedure. • Doffing – Hold glove bead and pull toward the finger until the glove come off. • Where relevant, a list of the substances contained in the glove which are known to cause allergies, per listed in Annex G of EN ISO 21420:2020, shall be supplied on request. • Components used in glove manufacturing may cause allergic reactions in some users. If allergic reactions occur, seek for medical advice immediately. • In storage, avoid excessive heat. Open box should be shielded from exposure to direct sun or fluorescent lighting. Gloves are packed in dispenser which is suitable for transport. Keep the gloves in box when not in use.

| Minimum Breakthrough Time (min) >240min | Chemotherapy Drug & Concentration   |
|---|---|
|   | Cisplatin 1.0 mg/ml, Cyclophosphamide (Cytoxan) 20.0 mg/ml, Cytarabine 100 mg/ml, Dacarbazine (DTIC) 10.0 mg/ml, Doxorubicin Hydrochloride 2.0 mg/ml, Etoposide 20.0 mg/ml, Fluorouracil 50.0 mg/ml, Ifosfamide 50.0 mg/ml, Methotrexate 25.0 mg/ml, Mitomycin 0.5 mg/ml, Mitoxantrone 2.0 mg/ml, Paclitaxel (Taxol) 6.0 mg/ml, Vincristine Sulfate 1.0 mg/ml |
|   | Fentanyl citrate and concentration  |
|   | Fentanyl citrate injection (100 mcg/2ml)  |

30.2min Thiotepa (10.0 mg/ml)  
10.1min Carmustine (BCNU) (3.3 mg/ml)

**Warning: Not recommended for use with Carmustine and Thiotepa.**  
Tested for use with Chemotherapy Drugs using ASTM D6978.

| Resistance to Permeation by Chemicals | Level | Mean Degradation (%) |
|---------------------------------------|-------|----------------------|
| *4% Chlorhexidine Digluconate         | 6     | 19.0                 |
| 40% Sodium Hydroxide (K)              | 6     | -42.9                |
| 10-13% Sodium Hypochlorite            | 6     | 14.7                 |
| 50% Sulphuric Acid                    | 6     | -20.5                |
| 5% Ethidium Bromide                   | 6     | 3.4                  |
| 50% Glutaraldehyde                    | 6     | 27.4                 |
| 0.1% Phenol                           | 6     | 33.8                 |
| 1.5% Methanol in Water                | 6     | 21.9                 |
| 3% Povidone-iodine                    | 6     | 33.7                 |
| 10% Sodium Percarbonate               | 6     | 15.4                 |
| 10% Acetic Acid                       | 4     | 66.7                 |
| 37% Formaldehyde (T)                  | 3     | 5.0                  |
| 30% Hydrogen Peroxide (P)             | 2     | 22.8                 |
| 25% Ammonium Hydroxide (O)            | 0     | -52.0                |
| 65% Nitric Acid (M)                   | 0     | 97.6                 |
| 70% Isopropanol                       | 0     | 62.2                 |
| 35% Ethanol                           | 0     | 93.9                 |
| 99% Acetic Acid (N)                   | 0     | 93.9                 |

\* Permeation rate 7µg/cm²/min

Permeation Performance Level & Measured Breakthrough Time (minutes)  
0 > \* 1 > 10 min, 2 > 30 min, 3 > 60 min, 4 > 120 min, 5 > 240 min, 6 > 480 min

\*Indicates that the glove falls below the minimum performance level as stated in EN ISO 374-1:2016 +A1:2018 for the given individual hazard.



PAP  
RECYCLABLE  
PAPER MATERIAL  
G-LF-XXXXXX-F-R0  
Last update in 2022

### FR POWDER FREE NITRILE EXAMINATION GLOVES

• Non sterile • Single Use  
• Recommended for medical use

Règlement sur les dispositifs médicaux (UE) 2017/745 et règlement sur les équipements de protection individuelle (UE) 2016/425 (catégorie III). • Règlement sur les dispositifs médicaux de 2002 (SI 2002 No. 618, tel que modifié) (UK MDR 2002) • Organisme notifié de l'UE pour le (module B) et le module C2, est SATRA Technology Europe Limited (2777) • Organisme agréé Royaume-Uni pour le (module B) et le module C2 est SATRA Technology Center Limited (A80321). • La déclaration de conformité de l'UE et la déclaration de conformité du Royaume-Uni sont accessibles à l'adresse [www.intouchcares.com](http://www.intouchcares.com). • Ces informations ne reflètent pas la durée réelle de la protection sur le lieu de travail et la différenciation entre les mélanges et les produits chimiques purs. • La résistance chimique a été évaluée dans des conditions de laboratoire à partir d'échantillons prélevés sur la paume uniquement (sauf dans les cas où le gant mesure 400 mm ou plus - où la manchette est également testée) et ne concerne que le produit chimique testé. Elle peut être différente si le produit chimique est utilisé dans un mélange. • Il est recommandé de vérifier que les gants sont adaptés à l'utilisation prévue car les conditions sur le lieu de travail peuvent différer de l'essai de type en fonction de la température, de l'abrasion et de la dégradation. • Lorsque est utilisé le gant de protection peut offrir une moindre résistance au produit chimique dangereux en raison des modifications de ses propriétés physiques. Les mouvements, les accrochages, les frottements, la dégradation causés par le contact chimique, etc peuvent réduire considérablement la durée d'utilisation réelle. Pour les produits chimiques corrosifs, la dégradation peut être le facteur le plus important à prendre en compte dans le choix de gant de protection aux produits chimiques. • Avant l'utilisation, inspectez les gants pour détecter tout défaut ou imperfection. • EN ISO 374-4:2019 Les niveaux de dégradation indiquent le changement de la résistance à la perforation des gants après exposition au produit chimique de référence. • La résistance à la pénétration a été évaluée dans des conditions de laboratoire et ne concerne que les spécimens testés. • Enfilage - Tenez le gant par le talon d'une main. Alignez le pouce du gant avec le pouce de l'autre main et glissez votre main dans le gant, un doigt dans chaque doigt et tirez sur la paume du gant pour obtenir un bon ajustement. Enfilez l'autre gant en suivant la même procédure. • Enlever le gant - Tenir le talon du gant et tirer vers le doigt jusqu'à ce que le gant se détache. • Le cas échéant, une liste des substances contenues dans le gant et connues pour provoquer des allergies, telles qu'énumérées à l'annexe G de la norme EN ISO 21420:2020, doit être fournie sur demande. • Les composants utilisés dans la fabrication des gants peuvent provoquer des réactions allergiques chez certains utilisateurs. En cas de réaction allergique, consulter immédiatement un médecin. • Lors du stockage, éviter toute chaleur excessive. La boîte ouverte doit être protégée de l'exposition directe au soleil ou à un éclairage fluorescent. Les gants sont emballés dans un distributeur qui convient au transport. Conservez les gants dans leur boîte lorsqu'ils ne sont pas utilisés.

| Temps de détection minimal de la perçure > 240min | Médicament de chimiothérapie et concentration  |
|---|--|
|   | Cisplatine 1.0 mg/ml, Cyclophosphamide (Cytoxan) 20.0 mg/ml, Cytarabine 100 mg/ml, Dacarbazine (DTIC) 10.0 mg/ml, Doxorubicin Hydrochloride 2.0 mg/ml, Etoposide 20.0 mg/ml, Fluorouracil 50.0 mg/ml, Ifosfamide 50.0 mg/ml, Methotrexate 25.0 mg/ml, Mitomycine 0.5 mg/ml, Mitoxantrone 2.0 mg/ml, Paclitaxel (Taxol) 6.0 mg/ml, Sulfate de Vincristine 1.0 mg/ml |
|   | Citrate de fentanyl et concentration   |
|   | Injection de citrate de fentanyl (100 mcg/2ml)   |

30.2min Thiotepa (10.0 mg/ml)  
10.1min Carmustine (BCNU) (3.3 mg/ml).

**Avertissement : Non recommandé pour une utilisation avec Carmustine et Thiotepa.**  
Testé pour une utilisation avec les médicaments de chimiothérapie selon ASTM D6978.

| Résistance à la perméation par les produits chimiques | Niveau | Moyenne Dégradation (%) |
|---|--------|-------------------------|
| *4% Digluconate de chlorhexidine                      | 6      | 19.0                    |
| Hydroxyde de sodium à 40% (K)                         | 6      | -42.9                   |
| 10-13% Hypochlorite de sodium                         | 6      | 14.7                    |
| 50% Acide sulfurique                                  | 6      | -20.5                   |
| 5% Bromure d'éthidium                                 | 6      | 3.4                     |
| 50% Glutaraldéhyde                                    | 6      | 27.4                    |
| 0.1% Phénol   | 6      | 33.8                    |
| 1.5% Méthanol dans l'eau                              | 6      | 21.9                    |
| 3% Povidone-iodée                                     | 6      | 33.7                    |
| 10% Acétate de sodium                                 | 6      | 15.4                    |
| 10% Acide acétique                                    | 4      | 66.7                    |
| 37% Formaldéhyde (T)                                  | 3      | 5.0                     |
| 30% Peroxyde d'hydrogène (P)                          | 2      | 22.8                    |
| 25% D'hydroxyde d'ammonium (O)                        | 0      | -52.0                   |
| 65% Acide azotique (M)                                | 0      | 97.6                    |
| 70% Isopropanol                                       | 0      | 62.2                    |
| 35% Ethanol   | 0      | 93.9                    |
| 99% Acide acétique à 99 % (N)                         | 0      | 93.9                    |

\* Taux de perméation 7µg/cm²/min

Niveau de performance de perméation et temps de percée mesurés (minutes)  
0 > \* 1 > 10 min, 2 > 30 min, 3 > 60 min, 4 > 120 min, 5 > 240 min, 6 > 480 min

\*Indique que le gant est inférieur au niveau de performance minimum tel qu'indiqué dans la norme EN ISO 374-1:2016 +A1:2018 pour le risque individuel donné.

### RO POWDER FREE NITRILE EXAMINATION GLOVES

• Non sterile • Single Use  
• Recommended for medical use

Regulamentul privind Dispozitivele Medicale (UE) 2017/745 și Regulamentul privind Echipamentul Individual de Protecție (UE) 2016/425 (Categorie III). • Regulamentul privind Dispozitivele Medicale 2002 (SI 2002 Nr. 618, cu modificări) (UK MDR 2002) • Organismul Notificat UE pentru (Modulul B) și Modulul C2: SATRA Technology Europe Limited (2777) • Organismul Notificat MB pentru (Modulul B) și Modulul C2: SATRA Technology Center Limited (A80321) • Declarația de Conformitate UE și Declarația de Conformitate MB este accesibilă la adresa [www.intouchcares.com](http://www.intouchcares.com). • Informația dată nu se referă la protecția locului de muncă și siguranța la diferite amestecuri din produse chimice. • Rezistența chimică a fost evaluată în condiții de laborator, mostrele folosite au fost selectate doar din palmă, cu excepția cazurilor când mărșă are 400 mm și mai mult - unde și manșeta este testată) și se referă doar la substanța chimică testată. Rezultatele pot fi diferite dacă este folosit un amestec de substanțe chimice. • Se recomandă de a verifica dacă mârșă sunt potrivite pentru a fi folosite în scopul propus, deoarece condițiile locului de muncă pot fi diferite de tipul testărilor efectuate și se pot diferenția prin temperatură, abraziune și degradare. • Mârșă de protecție, în timpul utilizării, pot oferi o rezistență mai mică la substanțele chimice periculoase din cauza modificărilor proprietăților fizice la acțiunea acestor compuși chimici. Mișcările, strângerea, frecarea, degradarea cauzată de interacțiunea chimică etc. poate reduce semnificativ timpul real de utilizare. Pentru produsele chimice corozive, degradarea poate fi cel mai important factor pentru a fi luat în considerare la selectarea mârșă rezistente la produsele chimice. • Înainte de folosire, verificați mârșă la lipsa defectelor și imperfecțiunilor. • EN ISO 374-4:2019 Nivelurile de degradare indică modificarea rezistenței mârșă la perforare după expunerea la substanțele chimice. • Rezistența la penetrare a fost evaluată în baza condițiilor de laborator și se referă doar la specișănele testate. • Înbrăcarea - Apucați mârșă de margine cu o mârșă. Introduceți degetul mare al mârșă pe degetul mare al celelalte mârșă și trageți mârșă în mârșă, fiecare deget al mârșă în degetul mârșă. Trageți astfel mârșă încât să se potrivească. Înbrăcați celelalte mârșă după același scenariu. • Dezbrăcarea - Țineți marginea mârșă și trageți de pe degete până mârșă va iesi. • Unde e cazul, se va oferi la cerere lista componentelor mârșă care sunt recunoscute ca alergeni, menționate în Anexa G a EN ISO 21420:2020. • Componentele folosite la producerea mârșă pot cauza reacții alergice la unii utilizatori. Dacă se produce o reacție alergică, adresă-vă urgent medicului. • Mârșă se vor păstă la loc ferit de căldură în exces. Căută deschișă se va proteja de expunerea directă la soare sau lumină fluorescentă. • Mârșă sunt ambalate în cutie care se potrivește pentru transportare. Păstrați mârșă în cutie atunci când nu sunt folosite.

| Temp minim de detectare a perforării > 240min | Medicamente chimioterapice și concentrație   |
|---|--|
|   | Cisplatina 1.0 mg/ml, Ciclofosfamidă (Cytoxan) 20.0 mg/ml, Citarabina 100 mg/ml, Dacarbazina (DTIC) 10.0 mg/ml, Doxorubicina clorhidrat 2.0 mg/ml, Etoposid 20.0 mg/ml, Ios.0 mg/ml, 50.0 mg/ml, Metotrexat 25.0 mg/ml, Mitomicina 0.5 mg/ml, Mitoxantrona 2.0 mg/ml, Paclitaxel (Taxol) 6.0 mg/ml Sulfat de vincristina 1.0 mg/ml |
|   | Citrat de fentanil și concentrație   |
|   | Injecție cu citrat de fentanil (100 mcg/2ml)   |

30.2min Thiotepa (10.0 mg/ml)  
10.1min Carmustină (BCNU) (3.3 mg/ml).

**Atenție: Nu se recomandă folosirea cu Carmustină și Thiotepa.**  
Testate la folosirea cu Medicamente chimioterapice folosind ASTM D6978.

| Rezistența Permeabilității Produselor Chimice | Nivel | Degradare medie (%) |
|---|-------|---------------------|
| *4% Digluconat de clorhexidină                | 6     | 19.0                |
| 40% Hidroxid de sodiu (K)                     | 6     | -42.9               |
| 10-13% Hipoclorit de sodiu                    | 6     | 14.7                |
| 50% Acid sulfuric                             | 6     | -20.5               |
| 5% Bromură de etidiu                          | 6     | 3.4                 |
| 50% Glutaraldehidă                            | 6     | 27.4                |
| 0.1% Fenol                                    | 6     | 33.8                |
| 1.5% Soluție apoasă de metanol                | 6     | 21.9                |
| 3% Iod-Povidonă                               | 6     | 33.7                |
| 10% Percarbonat de sodiu                      | 6     | 15.4                |
| 10% Acid acetic                               | 4     | 66.7                |
| 37% Formaldehidă (T)                          | 3     | 5.0                 |
| 30% Peroxid de hidrogen (P)                   | 2     | 22.8                |
| 25% Hidroxid de amoniu (O)                    | 0     | -52.0               |
| 65% Acid azotic (M)                           | 0     | 97.6                |
| 70% Izopropanol                               | 0     | 62.2                |
| 35% Etanol                                    | 0     | 93.9                |
| 99% Acid acetic (N)                           | 0     | 93.9                |

\* Rata permeabilității 7µg/cm²/min

Nivel de Performanță al Permeabilității și Timpul Măsurat de Străpungere (minute)  
0 > \* 1 > 10 min, 2 > 30 min, 3 > 60 min, 4 > 120 min, 5 > 240 min, 6 > 480 min

\*Indică faptul că mârșă este sub nivelul minim de performanță după cum se indică în EN ISO 374-1:2016 +A1:2018 pentru pericolul dat individual.

50mm

# intouch™

## POWDER FREE LATEX EXAMINATION GLOVES

EN : USER INFORMATION  
DE : NUTZERINFORMATION  
FR : FICHE D'INFORMATION  
RO : INFORMAȚII UTILIZATOR



Available Size

XS  
S  
M  
L  
XL



Last update in August 2022

110mm

## EN POWDER FREE LATEX EXAMINATION GLOVES

• Non sterile • Single Use  
• Recommended for medical use

Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III) • Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) • EU Notified Body for (Module B) and Module C2: SATRA Technology Europe Limited (2777) • UK Approved Body for (Module B) and Module C2: SATRA Technology Center Limited (A80321) • EU Declaration of Conformity & UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com) • This information does not reflect the actual duration of protection in the workplace and the differentiation between mixtures and pure chemicals. • The chemical resistance has been assessed under laboratory conditions from samples taken from the palm only (except in cases where the glove is equal to or over 400mm – where the cuff is tested also) and relates only to the chemical tested. It can be different if the chemical used is a mixture. • It is recommended to check that the gloves are suitable for the intended use because the conditions at the workplace may differ from the type test depending on temperature, abrasion and degradation. • When used, protective glove may provide less resistance to the dangerous chemical due to changes in physical properties. Movements, snagging, rubbing, degradation caused by chemical contact etc. may reduce the actual use time significantly. For corrosive chemicals, degradation can be the most important factor to consider in selection of chemical resistant gloves. • Before usage, inspect the gloves for any defect or imperfections. • EN ISO 374-4:2019 Degradation levels indicate the change in puncture resistance of the gloves after exposure to the challenge chemical. • The penetration resistance has been assessed under laboratory conditions and relates only to the tested specimens. • Donning – Hold glove by the bead with one hand. Align the glove thumb with your other hand thumb and slide your hand into the glove, one finger into each glove finger. Pull by the opposite palm to get a good fit. Don the other glove by the same procedure. • Doffing – Hold glove bead and pull toward the finger until the glove come off. • Where relevant, a list of the substances contained in the glove which are known to cause allergies, per listed in Annex G of EN ISO 374-5:2016, shall be supplied on request. • Components used in glove manufacturing may cause allergic reactions in some users. If allergic reactions occur, seek for medical advice immediately. • In storage, avoid excessive heat. Open box should be shielded from exposure to direct sun or fluorescent lighting. Gloves are packed in dispenser which is suitable for transport. Keep the gloves in box when not in use.

| Resistance to Permeation by Chemicals | Level | Mean Degradation (%) |
|---------------------------------------|-------|----------------------|
| Diethylamine (G)                      | 0     | 7.2                  |
| 96% Sulphuric Acid (L)                | 0     | 100.0                |
| 40% Sodium Hydroxide (K)              | 6     | -14.9                |
| 30% Hydrogen Peroxide (P)             | 2     | -15.6                |
| 37% Formaldehyde (T)                  | 1     | -22.4                |

Permeation Performance Level & Measured Breakthrough Time (minutes) 0 > \*, 1 > 10 min, 2 > 30 min, 3 > 60 min, 4 > 120 min, 5 > 240 min, 6 > 480 min

\*Indicates that the glove falls below the minimum performance level as stated in EN ISO 374-1:2016 +A1:2018 for the given individual hazard.

50mm

## FR GANTS D'EXAMEN NITRILES SANS POUVRE

• Non stérile • Usage unique  
• Recommandés pour un usage médical

Règlement sur les dispositifs médicaux (UE) 2017/745 et règlement sur les équipements de protection individuelle (UE) 2016/425 (catégorie III). • Règlement sur les dispositifs médicaux de 2002 (SI) 2002 No. 618, tel que modifié (UK MDR 2002) • Organisme notifié de l'UE pour le (module B) et le module C2 est SATRA Technology Europe Limited (2777) • Organisme agréé au Royaume-Uni pour le (module B) et le module C2 est SATRA Technology Center Limited (A80321). • La déclaration de conformité de l'UE et la déclaration de conformité du Royaume-Uni sont accessibles à l'adresse [www.intouchcares.com](http://www.intouchcares.com). • Ces informations ne reflètent pas la durée réelle de la protection sur le lieu de travail et la différenciation entre les mélanges et les produits chimiques purs. • La résistance chimique a été évaluée dans des conditions de laboratoire à partir d'échantillons prélevés sur la paume uniquement (sauf dans les cas où le gant mesure 400 mm ou plus – ou la manchette est également testée) et ne concerne que le produit chimique testé. Elle peut être différente si le produit chimique est utilisé dans un mélange. • Il est recommandé de vérifier que les gants sont adaptés à l'utilisation prévue car les conditions sur le lieu de travail peuvent différer de l'essai de type en fonction de la température, de l'abrasion et de la dégradation. • Lorsqu'il est utilisé, le gant de protection peut offrir une moindre résistance au produit chimique dangereux en raison des modifications de ses propriétés physiques. Les mouvements, les accrochages, les frottements, la dégradation causée par le contact chimique, etc. peuvent réduire considérablement la durée d'utilisation réelle. Pour les produits chimiques corrosifs, la dégradation peut être le facteur le plus important à prendre en compte dans le choix de gants résistants aux produits chimiques. • Avant l'utilisation, inspectez les gants pour détecter tout défaut ou imperfection. • EN ISO 374-4:2019 Les niveaux de dégradation indiquent le changement de la résistance à la perforation des gants après exposition au produit chimique de référence. • La résistance à la pénétration a été évaluée dans des conditions de laboratoire et ne concerne que les spécimens testés. • Enfilage - Tenez le gant par le talon d'une main. Alignez le pouce du gant avec le pouce de l'autre main et glissez votre main dans le gant, un doigt dans chaque doigt du gant. Tirez sur la paume du gant pour obtenir un bon ajustement. Enfilez l'autre gant en suivant la même procédure. • Enlevez le gant - Tenez le talon du gant et tirez vers le doigt jusqu'à ce que le gant se détache. • Le cas échéant, une liste des substances contenues dans le gant et connues pour provoquer des allergies, telles qu'énumérées à l'annexe G de la norme EN ISO 374-5:2016, doit être fournie sur demande. • Les composants utilisés dans la fabrication des gants peuvent provoquer des réactions allergiques chez certains utilisateurs. En cas de réaction allergique, consultez immédiatement un médecin. • Lors du stockage, évitez toute chaleur excessive. La boîte ouverte doit être protégée de l'exposition directe au soleil ou à un éclairage fluorescent. Les gants sont emballés dans un distributeur qui convient au transport. Conservez les gants dans leur boîte lorsqu'ils ne sont pas utilisés.

| Résistance à la perméation par les produits chimiques | Niveau | Moyenne Dégradation (%) |
|---|--------|-------------------------|
| Diéthylamine (G)                                      | 0      | 7.2                     |
| 96% Acide sulfurique (L)                              | 0      | 100.0                   |
| 40% Hydroxyde de sodium (K)                           | 6      | -14.9                   |
| 30% Peroxyde d'hydrogène (P)                          | 2      | -15.6                   |
| 37% Formaldéhyde (T)                                  | 1      | -22.4                   |

Niveau de performance de perméation et temps de percée mesuré (minutes) 0 > \*, 1 > 10 min, 2 > 30 min, 3 > 60 min, 4 > 120 min, 5 > 240 min, 6 > 480 min

\*Indique que le gant est inférieur au niveau de performance minimum tel qu'indiqué dans la norme EN ISO 374-1:2016 +A1:2018 pour le risque individuel donné.

110mm

## RO MÂNUSI NITRIL NEPUDRATE PENTRU EXAMINARE

• Nesterile • De unică folosință  
• Recomandate a fi folosite în scop medical

Regulamentul privind Dispozitivele Medicale (UE) 2017/745 și Regulamentul privind Echipamentul Individual de Protecție (UE) 2016/425 (Categorie III) • Regulamentul privind Dispozitivele Medicale 2002 (SI) 2002 Nr. 618, cu modificări (UK MDR 2002) • Organism Notificat UE pentru (Modulul B) și Modulul C2: SATRA Technology Europe Limited (2777) • Organismul Notificat MB pentru (Modulul B) și Modulul C2: SATRA Technology Center Limited (A80321) • Declarația de Conformitate UE și Declarația de Conformitate MB este accesibilă la adresa [www.intouchcares.com](http://www.intouchcares.com). • Informația dată nu se referă la protecția locului de muncă și siguranța la diferite amestecuri din produse chimice. • Rezistența chimică a fost evaluată în condiții de laborator pe eșantioane prelevate doar din palmă, cu excepția cazurilor când mîna are 400 mm și mai mult – unde și manșeta este testată) și se referă doar la substanța chimică testată. Rezultatele pot fi diferite dacă este folosit un amestec de substanțe chimice. • Se recomandă de a verifica dacă mînușile sunt potrivite pentru a fi folosite în scopul propus, deoarece condițiile locului de muncă pot fi diferite de tipul testărilor efectuate și se pot diferenția prin temperatură, abraziune și degradare. • Mînușile de protecție, în timpul utilizării, pot oferi o rezistență mai mică la substanțele chimice periculoase din cauza modificărilor proprietăților fizice la acțiunea acestor compuși chimici. Mișcarea, strângerea, frecarea, degradarea poate fi cel mai important factor pentru a fi luat în considerare la selecția mînușilor rezistente la produsele chimice. • Înainte de folosire, verificați mînușile la lipsa defectelor și imperfecțiunilor. • EN ISO 374-4:2019 Nivelurile de degradare indică modificarea rezistenței mînușilor la perforare după expunerea la substanțele chimice. • Rezistența la penetrare a fost evaluată în baza condițiilor de laborator și se referă doar la speciile testate. • Înălțarea - Apucați mîna de margine cu o mînă. Introduceți degetul mare al mînușii pe degetul mare al celeilalte mîni și trageți mîna în mînușă, fiecare deget al mîinii în degetul mînușii. Trageți astfel mîna încît să se potrivească. Înălțarea celeilalte mînușii după același scenariu. • Dezbrăcarea - Țineți marginea mînușii și trageți de pe degete pînă mînușă va ieși. • Unde e cazul, se va oferi la cerere lista componentelor mînușii care sunt recunoscute ca alergeni, menționate în Anexa G a EN ISO 374-5:2016. • Componentele folosite la producerea mînușilor pot cauza reacții alergice la unii utilizatori. Dacă se produce o reacție alergică, adresați-vă urgent medicului. • Mînușile se vor păstra la loc ferit de căldură în exces. Cutia deschisă se va proteja de expunerea directă la soare sau lumină fluorescentă. • Mînușile sunt ambalate în cutie care se potrivește pentru transportare. Păstrați mînușile în cutie atunci cînd nu sunt folosite.

| Rezistența Permeabilității Produselor Chimice | Nivel | Degradare medie (%) |
|---|-------|---------------------|
| Diethylamine (G)                              | 0     | 7.2                 |
| 96% Acid sulfuric (L)                         | 0     | 100.0               |
| 40% Hidroxid de sodiu (K)                     | 6     | -14.9               |
| 30% Peroxid de hidrogen (P)                   | 2     | -15.6               |
| 37% Formaldehidă (T)                          | 1     | -22.4               |

Nivel de Performanță al Permeabilității și Timpul Măsurat de Străpungere (minute) 0 > \*, 1 > 10 min, 2 > 30 min, 3 > 60 min, 4 > 120 min, 5 > 240 min, 6 > 480 min

\*Indică faptul că mînușă este sub nivelul minim de performanță, după cum se indică în EN ISO 374-1:2016 +A1:2018 pentru pericolul dat individual.

Comfort and higher dexterity • Chemical permeation tested • Polymer coated • Made with natural rubber latex

Powder-free Examination Gloves

Comfort-care

LATEX


XS  
5-6  
100 gloves  
by weight

LATEX

Comfort-care

Powder-free Examination Gloves

PS54



NATURAL COLOUR  
XS  
5-6  
100 gloves  
by weight

LATEX  
Comfort-care  
Powder-free Examination Gloves

NATURAL COLOUR  
XS  
5-6  
100 gloves  
by weight

XS  
5-6  
100 gloves  
by weight

NATURAL COLOUR

LATEX  
Comfort-care  
Powder-free Examination Gloves

XS

LATEX

Comfort-care

Powder-free Examination Gloves

- Gants d'examen en latex sans poudre
- Guderfrei untersuchungshandschuhe aus latex
- Mănuși latex nepudrate pentru examinare

XS  
5-6  
100 gloves  
by weight

XS

LATEX

Comfort-care

Powder-free Examination Gloves

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PF NR

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0321), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This product contains natural rubber latex which may cause allergic reactions, including anaphylactic responses. This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** (273178-M) Tel +603 3392 3013  
Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3 1/2, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.com](mailto:info@advena.com)  
Tower Business Centre, 2nd Floor, Tower Street, Swatara, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.


Made in Malaysia



955256614668  
REF  
IMPS54YWA-XS

| Chemicals                 | Level | Mean degradation |
|---------------------------|-------|------------------|
| Diethylamine (G)          | 0     | -7.2%            |
| 96% Sulphuric acid (L)    | 0     | 100.0%           |
| 40% Sodium hydroxide (K)  | 6     | -14.9%           |
| 30% Hydrogen peroxide (P) | 2     | -15.6%           |
| 37% Formaldehyde (T)      | 1     | -22.4%           |

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1: 2016 +A1: 2018.  
Level 1 represents > 10 min      Level 2 represents > 60 min      Level 3 represents > 240 min  
Level 4 represents > 30 min      Level 5 represents > 120 min      Level 6 represents > 480 min




Comfort and higher dexterity • Chemical permeation tested • Polymer coated • Made with natural rubber latex

**LATEX**  
Comfort-care  
Powder-free Examination Gloves

**S**  
6-7  
100 gloves  
by weight

**LATEX**  
*Comfort-care*  
Powder-free Examination Gloves

PS54



**S**  
6-7  
100 gloves  
by weight

**LATEX**  
*Comfort-care*  
Powder-free Examination Gloves

NATURAL COLOUR  
**S**  
6-7  
100 gloves  
by weight

**S**  
6-7  
100 gloves  
by weight

NATURAL COLOUR

**LATEX**  
*Comfort-care*  
Powder-free Examination Gloves

**intouch**  
TM

**S**

**LATEX**  
*Comfort-care*  
Powder-free Examination Gloves

- Gants d'examen en latex sans poudre
- Guderfrei untersuchungshandschuhe aus latex
- Mănuși latex nepudrate pentru examinare

**S**  
6-7  
100 gloves  
by weight

**S**

**LATEX**  
*Comfort-care*  
Powder-free Examination Gloves

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PF-NR

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0321), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com)

This product contains natural rubber latex which may cause allergic reactions, including anaphylactic responses. This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** (273178-M) Tel +603 3392 3013  
Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3 1/2, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.mt](mailto:info@advena.mt)  
Tower Business Centre, 2nd Floor, Tower Street, Swatar, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia




9555256614675

REF  
IMPS54YWA-S

| Chemicals                 | Level | Mean degradation |
|---------------------------|-------|------------------|
| Diethylamine (G)          | 0     | 7.2%             |
| 96% Sulphuric acid (L)    | 0     | 100.0%           |
| 40% Sodium hydroxide (K)  | 6     | -14.9%           |
| 30% Hydrogen peroxide (P) | 2     | -15.6%           |
| 37% Formaldehyde (T)      | 1     | -22.4%           |

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1: 2016 +A1: 2018  
Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min



REF  
IMPS54YWA-S



Comfort and higher dexterity • Chemical permeation tested • Polymer coated • Made with natural rubber latex

Powder-free Examination Gloves

LATEX


M  
7 - 8  
100 gloves  
by weight

LATEX

Comfort-care

PS54

Powder-free Examination Gloves



M  
7 - 8  
100 gloves  
by weight

LATEX  
Comfort-care  
Powder-free Examination Gloves

NATURAL COLOUR  
M  
7 - 8  
100 gloves  
by weight

M  
7 - 8  
100 gloves  
by weight  
NATURAL COLOUR

LATEX  
Comfort-care  
Powder-free Examination Gloves

M

LATEX

Comfort-care

Powder-free Examination Gloves

- Gants d'examen en latex sans poudre
- Guderfrei untersuchungshandschuhe aus latex
- Mănuși latex nepudrate pentru examinare

M  
7 - 8  
100 gloves  
by weight

M

LATEX

Comfort-care

Powder-free Examination Gloves

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonsilla, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PF NR.

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0321), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This product contains natural rubber latex which may cause allergic reactions, including anaphylactic responses. This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** (27317840) Tel: +603 3392 3013  
Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3 1/2, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email: [info@advena.mt](mailto:info@advena.mt)  
Tower Business Centre, 2nd Floor, Tower Street, Swatar, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email: [info@advenamedical.com](mailto:info@advenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia




9555256614682

REF  
IMPS54YWA-M

| Chemicals                 | Level | Mean degradation |
|---------------------------|-------|------------------|
| Diethylamine (G)          | 0     | -7.2%            |
| 96% Sulphuric acid (L)    | 0     | 100.0%           |
| 40% Sodium hydroxide (K)  | 6     | -14.9%           |
| 30% Hydrogen peroxide (P) | 2     | -15.6%           |
| 37% Formaldehyde (T)      | 1     | -22.4%           |

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1:2016 «A1: 2018»  
Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min



Comfort and higher dexterity • Chemical permeation tested • Polymer coated • Made with natural rubber latex

Powder-free Examination Gloves

Comfort-care

LATEX

8-9  
100 gloves  
by weight

LATEX

Comfort-care

Powder-free Examination Gloves

PS54


LATEX  
Comfort-care  
Powder-free Examination Gloves

NATURAL COLOUR

8-9  
100 gloves  
by weight



Recommended for medical use



NATURAL COLOUR

8-9  
100 gloves  
by weight

8-9  
100 gloves  
by weight

NATURAL COLOUR

LATEX  
Comfort-care  
Powder-free Examination Gloves

intouch™

LATEX

Comfort-care

Powder-free Examination Gloves

- Gants d'examen en latex sans poudre
- Guderfrei untersuchungshandschuhe aus latex
- Mănuși latex nepudrate pentru examinare

8-9  
100 gloves  
by weight

LATEX

Comfort-care

Powder-free Examination Gloves

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PF NR

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0321), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This product contains natural rubber latex which may cause allergic reactions, including anaphylactic responses. This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** 07378849 Tel +603 3392 3013  
Wiema KGSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3k, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.mt](mailto:info@advena.mt)  
Tower Business Centre, 2nd Floor, Tower Street, Swatar, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@gadvenamedical.com](mailto:info@gadvenamedical.com)  
Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia




9555256614699

REF  
IMPS54YWA-L

| Chemicals                 | Level | Mean degradation |
|---------------------------|-------|------------------|
| Diethylamine (G)          | 0     | 7.2%             |
| 96% Sulphuric acid (L)    | 0     | 100.0%           |
| 40% Sodium hydroxide (K)  | 6     | -14.9%           |
| 30% Hydrogen peroxide (P) | 2     | -15.6%           |
| 37% Formaldehyde (T)      | 1     | -22.4%           |

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1: 2016 +A1: 2018  
Level 1 represents > 10 min Level 3 represents > 60 min Level 5 represents > 240 min  
Level 2 represents > 30 min Level 4 represents > 120 min Level 6 represents > 480 min



LOT




Comfort and higher dexterity - Chemical permeation tested - Polymer coated - Made with natural rubber latex  
 Powder-free Examination Gloves  
**LATEX**  
 Comfort-care

**XL**  
 9 - 10  
 100 gloves  
 by weight

**LATEX** **PS54**  
 Comfort-care  
 Powder-free Examination Gloves

**LATEX**  
 Comfort-care  
 Powder-free Examination Gloves

**XL**  
 9 - 10  
 100 gloves  
 by weight  
 NATURAL COLOUR



NATURAL COLOUR  
**XL**  
 9 - 10  
 100 gloves  
 by weight

**intouch**<sup>TM</sup>

**LATEX**  
 Comfort-care  
 Powder-free Examination Gloves

**XL**

**LATEX**  
 Comfort-care  
 Powder-free Examination Gloves

**XL**  
 9 - 10  
 100 gloves  
 by weight

**XL**

- Gants d'examen en latex sans poudre
- Guderfrei untersuchungshandschuhe aus latex
- Mănuși latex nepudrate pentru examinare

**LATEX**  
 Comfort-care  
 Powder-free Examination Gloves

In compliance with Medical Device Regulation (EU) 2017/745 & Personal Protective Equipment Regulation (EU) 2016/425 (Category III). Notified Body responsible for PPE EU Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Europe Limited (2777) Bracetown Business park, Clonee, Dublin 15, D15 YN2P, Ireland. EU Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com). Product reference: PF-NR

In compliance with Medical Devices Regulations 2002 (SI 2002 No. 618, as amended) (UK MDR 2002) and PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Approved Body responsible for PPE UKCA Type Examination (Module B) and Module C2 On-going Conformity Assessment is SATRA Technology Center Limited (AB0321), Wyndham Way, Kettering NN16 8SD, United Kingdom. In compliance with PPE Regulation (EU) 2016/425 as retained in UK Law and amended. UK Declaration of Conformity is accessible at [www.intouchcares.com](http://www.intouchcares.com).

This product contains natural rubber latex which may cause allergic reactions, including anaphylactic responses. This glove product is intended to be worn on the hand to provide a barrier protection against risks associated with contact with certain chemicals, microorganisms & other contaminants.

User information sheet is enclosed in this package.

**KOSSAN INTERNATIONAL SDN. BHD.** 07917846 | Tel +603 3392 3013  
 Wisma KOSSAN, Lot 782, Jalan Sungai Putus, Off Batu 3 1/2, Jalan Kapar, 42100 Klang, Selangor, Malaysia.

**ADVENA LIMITED** Email [info@advena.mt](mailto:info@advena.mt)  
 Tower Business Centre, 2nd Floor, Tower Street, Swatar, BKR 4013, Malta.

**UKRP ADVENA LIMITED UK** Email [info@advenamedical.com](mailto:info@advenamedical.com)  
 Pure Offices, Plato Close, Tachbrook Park, Warwick CV34 6WE, United Kingdom.

Made in Malaysia



9555256614705

**REF**  
 IMPS54YWA-XL

| Chemicals                 | Level | Mean degradation |
|---------------------------|-------|------------------|
| Diethylamine (G)          | 0     | 7.2%             |
| 96% Sulphuric acid (L)    | 0     | 100.0%           |
| 40% Sodium hydroxide (K)  | 6     | -14.9%           |
| 30% Hydrogen peroxide (P) | 2     | -15.6%           |
| 37% Formaldehyde (T)      | 1     | -22.4%           |

Level 0 represents below minimum permeation performance level as stated in EN ISO 374-1: 2016 +A1: 2018  
 Level 1 represents > 10 min  
 Level 2 represents > 30 min  
 Level 3 represents > 60 min  
 Level 4 represents > 120 min  
 Level 5 represents > 240 min  
 Level 6 represents > 480 min

