

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
21003760- İNG
02-21

TEST RESULTS

TEST METHOD: EN 13795-1:2019

SURGICAL CLOTHING AND DRAPES –REQUIREMENTS AND TEST METHODS

ANNEX 1: SURGICAL CLOTHING AND DRAPES;

TENSILE STRENGTH; EN 29073-3:1996

Instron 5969 (Load: 50 kN), Strip Method.

Speed: 100 mm/min±10, Gauge length 200 mm.

Pre-load was not applied. Without wetting samples.

The average results are given for weft and warp direction of five samples

Performed in the conditioned room ($20\pm2^{\circ}\text{C}$ -65%±4).

Dry ;

RESULT

Weft	42,6 N
Warp	93,3 N

REQUIREMENT

≥ 20N (Dry)

≥ 20N (Dry)

BURSTING STRENGTH;; ISO 13938-1:1999

SDL ATLAS M229 tester. Test area: 30.5 mm diameter

Rate of increase in volume; 29 cm³/min.

The average results are given of five samples.

Performed in the conditioned room ($20\pm2^{\circ}\text{C}$ -65%±4).

Dry ;

RESULT

109,6 kPa

Height at Burst* 85,0 mm

REQUIREMENT

≥ 40 kPa (Dry)

WATER PERMEABILITY; ISO 811:2018

Hydrostatic Head Tester, Textest marka Fx 3000 model

Temperature of water 20°C. Pressure increase ratio 10 mbar/min.

Performed in the conditioned room ($20\pm2^{\circ}\text{C}$ -65%±4)

Sample 1
Sample 2
Sample 3
Sample 4
Sample 5

Average

RESULT

35,5 cmH₂O
34,3 cmH₂O
33,5 cmH₂O
34,0 cmH₂O
34,7 cmH₂O

34,4 cmH₂O

REQUIREMENT

≥ 10 cmH₂O

ZENMED TİBBİ CİHAZLAR
VE SAĞLIK ÜRÜNLERİ SAN. VE TİC. LTD.ŞTİ.
Mahmutbey Mah. 2567 Sk. No:1 İş Yeri No:11,21
Bağcılar / İSTANBUL / TÜRKİYE
Tel: 0212 445 45 25 Tic.Sic.No: 794704
Güneşli V.D: 997 06 1942