

2022EP6256

TEST REPORT

DATE OF RECEPTION

Date Format: dd/MM/yyyy 25/02/2022

DATE OF TESTS

Starting : 02/03/2022

Ending: 17/03/2022

APPLICANT

XM Textiles Europe UAB

Darius ir Gireno st. 42A Office 509

LT-02189 Vilnius

Att CERTIFICATION TEAM

REFERENCE OF SAMPLES

Reference by AITEX	Reference provided by the customer	Sample description
2022EP6256-S01	Fabric ref. UNITEC-200	Fabric

TESTS CARRIED OUT

- PRE-TREATMENT FOR INDUSTRIAL WASHING AND DRYING PROCEDURES FOR TEXTILE TESTING
- DETERMINATION OF CANCEROGENIC ARYLAMINES
- DETERMINATION THE pH VALUE OF AQUEOUS EXTRACT
- DETERMINATION OF BREAKING STRENGTH AND ELONGATION
- DETERMINATION OF TEAR RESISTANCE
- DETERMINATION OF DIMENSIONAL CHANGE IN WASHING AND DRYING
- FORMALDEHYDE

Tests marked with * are not included within the scope of the accreditation.

**DESCRIPTION OF SAMPLES**

Reference by AITEX: 2022EP6256-S01

Reference provided by the customer:

Fabric ref. UNITEC-200

Sample description:

Fabric ref. UNITEC-200

Composition and percentage 65% Polyester, 35% Cotton, , Twill 3/1

Weight 200gsm

Color White

Others (if any) XMT-21-144-ZHJ

Reference by AITEX	Reference provided by the customer
2022EP6256-S01.1	Fabric ref. UNITEC-200 AFTER WASH

The client has provided AITEX all the technical information about the articles to certify. All this information is enclosed in the Application Form



RESULTS

PRE-TREATMENT FOR INDUSTRIAL WASHING AND DRYING PROCEDURES FOR TEXTILE TESTING

Standard

EN ISO 15797:2018

Washing procedure

Table 4, procedure 1

Washing cycles

1

Washing temperature

85°C

Driying procedure

A (tumble dryer) - Industrial dryer 13010I12

Driying temperature

70°C

Reference

2022EP6256-S01

Test date**Start date**

03/03/2022

End date

04/03/2022

Dry mass of the samples (Kg)	Counterweight mass (Kg)	Counterweight type	Equipment
0.35	12.1	COTTON / POLYESTER	LAVADORA INDUSTRIAL 4 13535I05



RESULTS

DETERMINATION OF CANCEROGENIC ARYLAMINES

Standard

EN 14362-1:2017

Detection System according to

Gas Chromatograph 7890A

Testing Method

GC/MSD

Uncertainty

± 9 mg/Kg

Reference	Result (mg/Kg)
2022EP6256-S01	< 30

¹ Arylamines tested

Substance		
4-Aminobiphenyl	3,3'-Dimethylbenzidine	2,4-Diaminoanisole
Benzidine	3,3'-Dimethyl-4,4'-diaminodiphenylmethane	o-Anisidine
4-Chlor-o-toluidine	p-Cresidine	3,3'-Dichlorobenzidine
2-Naphthylamine	4,4'-Methylene-bis-2-chloraniline	2,4,5-Trimethylaniline
o-Aminoazotoluene	4,4'-Oxydianiline	4,4'-Diaminodiphenylmethane
2-Amino-4-nitrotoluene	4,4'-Thiodianiline	2,4- Toluylendiamine
p-Chloraniline	o-Toluidine	
3,3'-Dimethoxybenzidine	4-Aminoazobenzene	



RESULTS

DETERMINATION THE pH VALUE OF AQUEOUS EXTRACT

Standard

EN ISO 3071:2020

Determination date

03/03/2022

Extractor solution

KCl

pH Extractor solution

5.6

Temperature

(21)°C

Reference	pH	Uncertainty
2022EP6256-S01	4.20	±5%



RESULTS

DETERMINATION OF BREAKING STRENGTH AND ELONGATION

Standard

EN ISO 13934-1:2013

Equipment

INSTRON Dynamometer

Conditioned date

Start date 7/3/2022 **End date** 10/3/2022

Test date

Start date 07/03/2022 **End date** 10/03/2022

Gauge length

Warp:200 mm

Weft:200 mm

Pretension

Warp:5.0 N

Weft:5.0 N

Gauge speed

Warp:100 mm/min

Weft :100 mm/min

Atmosphere for conditioning

Temperature (20 ± 2) °C **Relative Humidity** (65 ± 4) %

Number of test specimens per material to be tested

Tested 5 **Rejected** 0

State of the specimens

Conditioned

Reference

2022EP6256-S01.1

Direction	Maximum force (N)	Medium strength	C.V.	Elongation to the maximum load(%)	Average elongation	C.V.
Warp	1600	1600	1.5	18.5	18	3.2
	1700			18.5		
	1600			18		
	1600			18		
	1700			17		
Weft	700	710	2.9	16	16.5	1.3
	730			16.5		
	700			16.5		
	710			16.5		
	740			16.5		

Uncertainty

± 5% assay value of the measured



RESULTS

DETERMINATION OF TEAR RESISTANCE

Standard

EN ISO 13937-2:2000

Equipment

INSTRON Dynamometer

Test date

Start date 07/03/2022 **End date** 10/03/2022

Conditioned date

Start date 7/3/2022 **End date** 10/3/2022

Atmosphere for conditioning

Temperature (20 ± 2) °C **Relative Humidity** (65 ± 4) %

Number of test specimens per material to be tested

Tested 5 **Rejected** 0

Reference

2022EP6256-S01.1

Tear	Specimen	Average load	Classification value (N)	C.V.
Lengthwise	32.5	33	25.9	2.8
	32.5			
	32.3			
	33.5			
	34.4			
Crosswise	27.4	27		
	26.4			
	26.9			
	26.5			
	25.9			

Uncertainty

±3.9% assay value of the measured



RESULTS

DETERMINATION OF DIMENSIONAL CHANGE IN WASHING AND DRYING

Standard

EN ISO 5077:2008

Preparation, marking and measuring of fabric specimens according to EN ISO 3759:2011

Start date 10/3/2022 **End date** 17/03/2022

Equipment

Washing machine (13535105)

Washing cycles

5

Washing temperature

85°C

Driying procedure

A (tumble dryer) - Industrial dryer 13010I12

Driying temperature

70°C

Uncertainty

± 0.4 %

Reference

2022EP6256-S01.1

Specimen	Direction	Dimensional change (%)	Direction	Average result - Dimensional change (%)
1	WARP	-3	WARP	-3
	WEFT	-1		
-	-	---	WEFT	-1
	-	---		

Note

Positive dimensional change indicates lengthening. Negative dimensional change indicates shrinkage



RESULTS

FORMALDEHYDE

Standard

EN ISO 14184-1:2011

Test date**Start date**

04/03/2022

End date

04/03/2022

Application range of the calibration straight line

15-600 mg/Kg

Reference	Formaldehyde (mg/Kg)	Uncertainty
2022EP6256-S01	5	± 11%



Lucia Martinez
Head of PPE and Ballistics department

Date: 21/03/2022 17:12:27

Digitally Signed by: LUCIA MARTINEZ MOLTO -

NIF: 21651425F

Liability clauses

- 1-AITEX is liable only for the results of the methods of analysis used, as expressed in the report and referring exclusively to the materials or samples indicated in the same which are in its possession, the professional and legal liability of the Centre being limited to these. Unless otherwise stated, the samples were freely chosen and sent by the applicant.
- 2-AITEX shall not be liable in any case of misuse of the test materials nor for undue interpretation or use of this document.
- 3-The Offer and / or Order to which the applicant gives approval through signature and seal, constitutes the Legally Executable Agreement in which AITEX is responsible for safeguarding and guaranteeing the absolute confidentiality of the management of all the information obtained or created during the performance of the contracted activities.
- 4-In the eventuality of discrepancies between reports, a check to settle the same will be carried out in the head offices of AITEX. Also, the applicants undertake to notify AITEX of any complaint received by them as a result of the report, exempting this Centre from all liability if such is not done, the periods of conservation of the samples being taken into account.
- 5-AITEX will provide at the request of the person concerned, the treatment of complaints procedure. In the event that you want to make it, direct it to: calidad@aitex.es.
- 6-AITEX is not responsible for the information provided by customers, which is reflected in the Report, and may affect the validity of the results.
- 7-AITEX is not responsible for an inadequate state of the sample received that could compromise the validity of the results, expressing such circumstance, in the test reports.
- 8-AITEX may include in its reports, analyses, results, etc., any other evaluation which it considers necessary, even when it has not been specifically requested.
- 9-The uncertainties of the tests, which are made explicit in the Results Report, have been estimated for a $k = 2$ (probability of coverage of 95%). If not informed, they are available to the client in AITEX.
- 10-The original materials and rests of samples, not subject to test, will be retained in AITEX during the twelve months following the issuance of the report, so that any check or claim which, in his case, wanted to make the applicant, should be exercised within the period indicated.
- 11-When a Declaration of Conformity is requested, if not indicated otherwise, the decision rule will be applied according to ILAC-G8 & ISO 10576-1, in case of ambiguity, or indeterminacy
- 12-This report may only be sent or delivered by hand to the applicant or to a person duly authorised by the same.
- 13-The results of the tests and the statement of compliance with the specification in this report refer only to the test sample as it has been analyzed / tested and not the sample / item which has taken the test sample.
- 14-The client must attend at all times, to the dates of the realization of the tests.
- 15-According to Resolution EA (33) 31, the test reports must include the unique identification of the sample, and any brand or label of the manufacturer may be added. It is not allowed to re-issue test reports of untested sample names (references), they can only be re-issued for error correction or inclusion of omitted data that were already available at the time of the test. The laboratory can not assume responsibility for declaring that the product with the new trade name / trademark is strictly identical to the one originally tested; This responsibility belongs to the client.
- 16-This report may not be partially reproduced without the written approval of the issuing laboratory.
- 17-AITEX laboratories do not carry out sampling, so that the results of the test reports are applicable to the sample as it was received.